



LNP™ FARADEX™ Compound AS002

Americas: COMMERCIAL

Also known as: LNP™ FARADEX™ Compound AS-1002

Product reorder name: AS002

LNP* FARADEX* AS002 is a compound based on ABS ressin containing 10% Stainless Steel. Added features of this material include: Electrically Conductive, EMI/RFI Shielding.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yield	430	kgf/cm ²	ASTM D 638
Tensile Stress, break	400	kgf/cm ²	ASTM D 638
Tensile Strain, yield	2.2	%	ASTM D 638
Tensile Strain, break	8.6	%	ASTM D 638
Tensile Modulus, 50 mm/min	30500	kgf/cm ²	ASTM D 638
Flexural Stress	770	kgf/cm ²	ASTM D 790
Flexural Modulus	28700	kgf/cm ²	ASTM D 790
Tensile Stress, yield	39	MPa	ISO 527
Tensile Stress, break	37	MPa	ISO 527
Tensile Strain, yield	2.2	%	ISO 527
Tensile Strain, break	3.3	%	ISO 527
Tensile Modulus, 1 mm/min	2500	MPa	ISO 527
Flexural Stress	66	MPa	ISO 178
Flexural Modulus	2500	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	29	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	5	cm-kgf/cm	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	121	cm-kgf	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	20	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	7	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	97	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	87	°C	ASTM D 648

(1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.

(2) Only typical data for selection purposes. Not to be used for part or tool design.

(3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

(4) Internal measurements according to UL standards.

(5) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(6) Needs hard coat to consistently pass 60 sec Vertical Burn.



LNP™ FARADEX™ Compound AS002

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
CTE, -40°C to 40°C, flow	7.92E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	7.56E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	7.8E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	9.6E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	91	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	78	°C	ISO 75/Af
PHYSICAL			
Density	1.12	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.2	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	18	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	27	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs (5)	0.18	%	ISO 294
Mold Shrinkage, xflow, 24 hrs (5)	0.27	%	ISO 294
Density	1.11	g/cm ³	ISO 1183
ELECTRICAL			
Volume Resistivity	1.E+02 - 1.E+06	Ohm-cm	ASTM D 257
Surface Resistivity	1.E+01 - 1.E+05	Ohm	ASTM D 257
Shielding Effectiveness @ 3mm	40 - 55	dB	SABIC Method

(1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.

(2) Only typical data for selection purposes. Not to be used for part or tool design.

(3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

(4) Internal measurements according to UL standards.

(5) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(6) Needs hard coat to consistently pass 60 sec Vertical Burn.



LNP™ FARADEx™ Compound AS002
Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.05 - 0.1	%
Melt Temperature	240 - 255	°C
Front - Zone 3 Temperature	255 - 265	°C
Middle - Zone 2 Temperature	230 - 245	°C
Rear - Zone 1 Temperature	210 - 220	°C
Mold Temperature	70 - 95	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm

(1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.

(2) Only typical data for selection purposes. Not to be used for part or tool design.
(3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.
(4) Internal measurements according to UL standards.
(5) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
(6) Needs hard coat to consistently pass 60 sec Vertical Burn.