



## LNP\* Stat-kon\* Compound AX02747 Asia Pacific: COMMERCIAL

Also known as: LNP\* Stat-kon\* Compound PDX-A-02747 Product reorder name: AX02747

LNP\* Stat-kon\* AX02747 is a compound based on Acrylonitrile Butadiene Styrene resin containing Proprietary Filler(s). Added features of this material include: Electrically Conductive.

| TYPICAL PROPERTIES 1       | TYPICAL VALUE   | UNIT                | STANDARD   |
|----------------------------|-----------------|---------------------|------------|
| MECHANICAL                 |                 |                     |            |
| Tensile Stress, break      | 1080            | kgf/cm <sup>2</sup> | ASTM D 638 |
| Tensile Strain, break      | 1               | %                   | ASTM D 638 |
| Tensile Modulus, 50 mm/min | 203800          | kgf/cm <sup>2</sup> | ASTM D 638 |
| Flexural Stress            | 1820            | kgf/cm <sup>2</sup> | ASTM D 790 |
| Flexural Modulus           | 184400          | kgf/cm <sup>2</sup> | ASTM D 790 |
| IMPACT                     |                 |                     |            |
| Izod Impact, notched, 23°C | 4               | cm-kgf/cm           | ASTM D 256 |
| PHYSICAL                   |                 |                     |            |
| Density                    | 1.24            | g/cm <sup>3</sup>   | ASTM D 792 |
| ELECTRICAL                 |                 | -                   |            |
| Surface Resistivity        | 1.E+01 - 1.E+03 | Ohm                 | ASTM D 257 |

 Typical values only. Variations within normal tolerances are possible for variose colours. All values are measured at least after 48 hours storage at 230C/50% relative humidity.
All properties, expect the melt volume rate are measured on injection moulded samples.
All samples are prepared according to ISO 294. 2) Only typical data for material selection purpose.Not to be used for part or tool design.
3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.
4) Own measurement according to UL.