



CYCOLAC™ RESIN DL100LG

REGION AMERICAS

DESCRIPTION

CYCOLAC DL100LG is a low gloss, high heat, high impact ABS/PC blend with low emission

TYPICAL PROPERTY VALUES

Revision 20170816

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	51	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	38	MPa	ASTM D 638
Tensile Stress, yld, Type I, 5 mm/min	47	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	40	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	4	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	12	%	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	4	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	85	%	ASTM D 638
Tensile Modulus, 50 mm/min	2240	MPa	ASTM D 638
Tensile Stress, yield, 5 mm/min	47	MPa	ISO 527
Tensile Stress, break, 5 mm/min	36	MPa	ISO 527
Tensile Stress, yield, 50 mm/min	51	MPa	ISO 527
Tensile Stress, break, 50 mm/min	39	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	4	%	ISO 527
Tensile Strain, break, 5 mm/min	50	%	ISO 527
Tensile Strain, yield, 50 mm/min	4	%	ISO 527
Tensile Strain, break, 50 mm/min	12	%	ISO 527
Tensile Modulus, 1 mm/min	2200	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	74	MPa	ISO 178
Flexural Modulus, 2 mm/min	2200	MPa	ISO 178
Hardness, H358/30	80	MPa	ISO 2039-1
IMPACT			
Izod Impact, notched, 23°C	380	J/m	ASTM D 256
Izod Impact, notched, -30°C	115	J/m	ASTM D 256
Izod Impact, notched 80*10*3 +23°C	45	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*3 -30°C	19	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 +23°C	28	kJ/m ²	ISO 180/1A

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Izod Impact, notched 80*10*4 -30°C	11	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	22	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm	11	kJ/m ²	ISO 179/1eA
THERMAL			
HDT, 1.82 MPa, 6.4 mm, unannealed	85	°C	ASTM D 648
CTE, -40°C to 40°C, flow	8.2E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	8.3E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate A/50	118	°C	ISO 306
Vicat Softening Temp, Rate A/120	120	°C	ISO 306
Vicat Softening Temp, Rate B/50	105	°C	ISO 306
Vicat Softening Temp, Rate B/120	107	°C	ISO 306
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	103	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	84	°C	ISO 75/Af
PHYSICAL			
Mold Shrinkage on Tensile Bar, flow (2) (5)	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 220°C/10.0 kgf	10	g/10 min	ASTM D 1238
Density	1.08	g/cm ³	ISO 1183
Melt Volume Rate, MVR at 220°C/10.0 kg	10	cm ³ /10 min	ISO 1133
Melt Volume Rate, MVR at 260°C/5.0 kg	12	cm ³ /10 min	ISO 1133
INJECTION MOLDING			
Drying Temperature	90 – 100	°C	
Drying Time	2 – 4	hrs	
Maximum Moisture Content	0.1	%	
Melt Temperature	250 – 280	°C	
Nozzle Temperature	245 – 275	°C	
Front - Zone 3 Temperature	250 – 280	°C	
Middle - Zone 2 Temperature	250 – 280	°C	
Rear - Zone 1 Temperature	230 – 260	°C	
Hopper Temperature	60 – 80	°C	
Mold Temperature	40 – 80	°C	

DISCLAIMER

The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC as referred to herein means any legal entity belonging to the group of companies headed by Saudi Arabia Basic Industries

+135-3858-6433 (GuangDong)
+188-1699-6168 (ShangHai)
+852-6957-5415 (HongKong)



Corporation.