



CYCOLAC™ RESIN FR15U

REGION ASIA

DESCRIPTION

Flame retardant ABS. Excellent indoor UV properties. Excellent moldability. UL94V-0/5VA rated. Elevated UL RTI rating.

TYPICAL PROPERTY VALUES

Revision 20170816

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	37	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	30	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	2.4	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	17	%	ASTM D 638
Tensile Modulus, 5 mm/min	2060	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	67	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2340	MPa	ASTM D 790
Tensile Stress, yield, 50 mm/min	41	MPa	ISO 527
Tensile Strain, break, 50 mm/min	21.9	%	ISO 527
Tensile Modulus, 1 mm/min	2210	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	63	MPa	ISO 178
Flexural Modulus, 2 mm/min	2260	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	213	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	28	J	ASTM D 3763
Izod Impact, notched 80*10*4 +23°C	12	kJ/m ²	ISO 180/1A
THERMAL			
Vicat Softening Temp, Rate B/50	93	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	86	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	75	°C	ASTM D 648
CTE, -40°C to 40°C, flow	9.E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	9.18E-05	1/°C	ASTM E 831
Vicat Softening Temp, Rate B/50	92	°C	ISO 306
Relative Temp Index, Elec	60	°C	UL 746B
Relative Temp Index, Mech w/impact	60	°C	UL 746B
Relative Temp Index, Mech w/o impact	60	°C	UL 746B
PHYSICAL			

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Specific Gravity	1.19	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm (5)	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 230°C/3.8 kgf	3.3	g/10 min	ASTM D 1238
Melt Viscosity, 200°C, 1000 sec-1	3200	Poise	ASTM D 3825
Density	1.19	g/cm ³	ISO 1183
Melt Flow Rate, 220°C/5.0 kg	7	g/10 min	ISO 1133
Melt Volume Rate, MVR at 220°C/10.0 kg	40	cm ³ /10 min	ISO 1133
ELECTRICAL			
Arc Resistance, Tungsten {PLC}	7	PLC Code	ASTM D 495
Hot Wire Ignition {PLC}	2	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	4	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	4	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	1	PLC Code	UL 746A
Volume Resistivity	> 1.E+14	Ohm-cm	IEC 60093
Dielectric Strength, in oil, 3.2 mm	20	kV/mm	IEC 60243-1
FLAME CHARACTERISTICS			
UL Recognized, 94V-0 Flame Class Rating (3)	1.49	mm	UL 94
UL Recognized, 94-5VA Rating (3)	2.79	mm	UL 94
INJECTION MOLDING			
Drying Temperature	80 – 90	°C	
Drying Time	2 – 4	hrs	
Drying Time (Cumulative)	8	hrs	
Maximum Moisture Content	0.1	%	
Melt Temperature	205 – 230	°C	
Nozzle Temperature	205 – 230	°C	
Front - Zone 3 Temperature	205 – 220	°C	
Middle - Zone 2 Temperature	200 – 210	°C	
Rear - Zone 1 Temperature	170 – 180	°C	
Mold Temperature	50 – 70	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	30 – 60	rpm	
Shot to Cylinder Size	50 – 70	%	
Vent Depth	0.038 – 0.051	mm	

DISCLAIMER

The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties. It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its



and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC as referred to herein means any legal entity belonging to the group of companies headed by Saudi Arabia Basic Industries Corporation.