



CYCOLAC™ RESIN INP362

REGION AMERICAS

DESCRIPTION

ABS, powder, high impact.

TYPICAL PROPERTY VALUES

Revision 20170816

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|--------------------------|----------------|-------------------|--------------|
| MECHANICAL | | | |
| Hardness, Shore D | 44 | - | ASTM D 2240 |
| PHYSICAL | | | |
| Specific Gravity | 0.97 | - | ASTM D 792 |
| Density | 0.98 | g/cm ³ | ISO 1183 |
| Mean Resin Particle Size | 700 | micrometer | SABIC method |
| Total NA Volatiles | 0.1 | % | SABIC method |
| Rubber | 62 | % | SABIC method |
| Bulk Density | 0.29 | g/cm ³ | ASTM D 1895 |

DISCLAIMER

The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC as referred to herein means any legal entity belonging to the group of companies headed by Saudi Arabia Basic Industries Corporation.

