



CYCOLAC™ Resin MGABS01

Americas: COMMERCIAL

Injection molding ABS. High impact, high gloss, good flow.

| TYPICAL PROPERTIES ¹ | TYPICAL VALUE | Unit | Standard |
|--|---------------|---------------------|--------------|
| MECHANICAL | | | |
| Tensile Stress, yld, Type I, 5 mm/min | 420 | kgf/cm ² | ASTM D 638 |
| Tensile Stress, brk, Type I, 5 mm/min | 320 | kgf/cm ² | ASTM D 638 |
| Tensile Strain, yld, Type I, 5 mm/min | 2.1 | % | ASTM D 638 |
| Tensile Strain, brk, Type I, 5 mm/min | 26 | % | ASTM D 638 |
| Tensile Modulus, 5 mm/min | 21000 | kgf/cm ² | ASTM D 638 |
| Flexural Stress, yld, 1.3 mm/min, 50 mm span | 690 | kgf/cm ² | ASTM D 790 |
| Flexural Modulus, 1.3 mm/min, 50 mm span | 21700 | kgf/cm ² | ASTM D 790 |
| IMPACT | | | |
| Izod Impact, notched, 23°C | 35 | cm-kgf/cm | ASTM D 256 |
| Instrumented Impact Total Energy, 23°C | 316 | cm-kgf | ASTM D 3763 |
| THERMAL | | | |
| Vicat Softening Temp, Rate B/50 | 98 | °C | ASTM D 1525 |
| HDT, 0.45 MPa, 3.2 mm, unannealed | 97 | °C | ASTM D 648 |
| HDT, 1.82 MPa, 3.2mm, unannealed | 82 | °C | ASTM D 648 |
| CTE, -40°C to 40°C, flow | 8.82E-05 | 1/°C | ASTM E 831 |
| CTE, -40°C to 40°C, xflow | 8.64E-05 | 1/°C | ASTM E 831 |
| Relative Temp Index, Elec | 60 | °C | UL 746B |
| Relative Temp Index, Mech w/impact | 60 | °C | UL 746B |
| Relative Temp Index, Mech w/o impact | 60 | °C | UL 746B |
| PHYSICAL | | | |
| Specific Gravity | 1.05 | - | ASTM D 792 |
| Mold Shrinkage, flow, 3.2 mm (5) | 0.5 - 0.8 | % | SABIC Method |
| Melt Flow Rate, 230°C/3.8 kgf | 3.7 | g/10 min | ASTM D 1238 |
| Melt Viscosity, 240°C, 1000 sec-1 | 2450 | poise | ASTM D 3825 |

(1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.

(2) Only typical data for selection purposes. Not to be used for part or tool design.

(3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

(4) Internal measurements according to UL standards.

(5) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(6) Needs hard coat to consistently pass 60 sec Vertical Burn.

Source GMD, last updated:

PLEASE CONTACT YOUR LOCAL SALES OFFICE FOR AVAILABILITY IN YOUR AREA.





CYCOLAC™ Resin MGABS01

Americas: COMMERCIAL

| TYPICAL PROPERTIES ¹ | TYPICAL VALUE | Unit | Standard |
|--|---------------|-------------------------|------------|
| PHYSICAL | | | |
| Melt Volume Rate, MVR at 220°C/10.0 kg | 15 | cm ³ /10 min | ISO 1133 |
| ELECTRICAL | | | |
| Arc Resistance, Tungsten {PLC} | 5 | PLC Code | ASTM D 495 |
| Hot Wire Ignition {PLC} | 3 | PLC Code | UL 746A |
| High Voltage Arc Track Rate {PLC} | 2 | PLC Code | UL 746A |
| High Ampere Arc Ign, surface {PLC} | 0 | PLC Code | UL 746A |
| Comparative Tracking Index (UL) {PLC} | 0 | PLC Code | UL 746A |
| FLAME CHARACTERISTICS | | | |
| UL Recognized, 94HB Flame Class Rating (3) | 1.52 | mm | UL 94 |

(1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.

(2) Only typical data for selection purposes. Not to be used for part or tool design.

(3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

(4) Internal measurements according to UL standards.

(5) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(6) Needs hard coat to consistently pass 60 sec Vertical Burn.

Source GMD, last updated:





CYCOLAC™ Resin MGABS01

Americas: COMMERCIAL

| PROCESSING PARAMETERS | TYPICAL VALUE | Unit |
|-----------------------------|---------------|------|
| Injection Molding | | |
| Drying Temperature | 80 - 95 | °C |
| Drying Time | 2 - 4 | hrs |
| Drying Time (Cumulative) | 8 | hrs |
| Maximum Moisture Content | 0.1 | % |
| Melt Temperature | 220 - 260 | °C |
| Nozzle Temperature | 220 - 260 | °C |
| Front - Zone 3 Temperature | 215 - 240 | °C |
| Middle - Zone 2 Temperature | 205 - 225 | °C |
| Rear - Zone 1 Temperature | 190 - 210 | °C |
| Mold Temperature | 50 - 70 | °C |
| Back Pressure | 0.3 - 0.7 | MPa |
| Screw Speed | 30 - 60 | rpm |
| Shot to Cylinder Size | 50 - 70 | % |
| Vent Depth | 0.038 - 0.051 | mm |

(1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.

(2) Only typical data for selection purposes. Not to be used for part or tool design.

(3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

(4) Internal measurements according to UL standards.

(5) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(6) Needs hard coat to consistently pass 60 sec Vertical Burn.

Source GMD, last updated:

