

CYCOLAC™ RESIN X11

REGION AMERICAS

DESCRIPTION

Automotive: High heat resistance. Excellent flow/impact balance. High gloss.

TYPICAL PROPERTY VALUES

Revision 20170816

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	42	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	33	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	2.6	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	27	%	ASTM D 638
Tensile Modulus, 5 mm/min	2370	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	71	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2290	MPa	ASTM D 790
Hardness, Rockwell R	104	-	ASTM D 785
Tensile Stress, yield, 50 mm/min	46	MPa	ISO 527
Tensile Stress, break, 50 mm/min	35	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	2.6	%	ISO 527
Tensile Strain, break, 50 mm/min	18	%	ISO 527
Tensile Modulus, 1 mm/min	2350	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	69	MPa	ISO 178
Flexural Modulus, 2 mm/min	2170	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	300	J/m	ASTM D 256
Izod Impact, notched, 23°C, 6.4mm	240	J/m	ASTM D 256
Izod Impact, notched 80*10*4 +23°C	25	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	10	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -40°C	9	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	25	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	11	kJ/m ²	ISO 179/1eA
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	99	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	86	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	93	°C	ASTM D 648



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Vicat Softening Temp, Rate B/50	104	°C	ISO 306
Vicat Softening Temp, Rate B/120	106	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	85	°C	ISO 75/Af
Relative Temp Index, Elec	60	°C	UL 746B
Relative Temp Index, Mech w/impact	60	°C	UL 746B
Relative Temp Index, Mech w/o impact	60	°C	UL 746B
PHYSICAL			
Specific Gravity	1.04	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm (5)	0.5 – 0.8	%	SABIC method
Melt Flow Rate, 230°C/3.8 kgf	3.5	g/10 min	ASTM D 1238
Melt Flow Rate, 260°C/5.0 kgf	18	g/10 min	ASTM D 1238
Melt Flow Rate, 220°C/10.0 kg	10	g/10 min	ISO 1133
FLAME CHARACTERISTICS			
UL Recognized, 94HB Flame Class Rating (3)	1.5	mm	UL 94
INJECTION MOLDING			
Drying Temperature	90 – 95	°C	
Drying Time	2 – 4	hrs	
Drying Time (Cumulative)	8	hrs	
Maximum Moisture Content	0.01	%	
Melt Temperature	230 – 275	°C	
Nozzle Temperature	230 – 275	°C	
Front - Zone 3 Temperature	230 – 255	°C	
Middle - Zone 2 Temperature	210 – 225	°C	
Rear - Zone 1 Temperature	195 – 210	°C	
Mold Temperature	50 – 80	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	30 – 60	rpm	
Shot to Cylinder Size	50 – 70	%	
Vent Depth	0.038 – 0.051	mm	

DISCLAIMER

The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC as referred to herein means any legal entity belonging to the group of companies headed by Saudi Arabia Basic Industries Corporation.

