

GELOY™ RESIN HRA222

REGION ASIA

DESCRIPTION

PC/ASA flame retardant, excellent weatherability.

TYPICAL PROPERTY VALUES

Revision 20170816

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	63	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	56	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	4.3	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	> 100	%	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	4.2	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	> 100	%	ASTM D 638
Tensile Stress, break, 50 mm/min	45	MPa	ISO 527
Tensile Strain, break, 5 mm/min	> 50	%	ISO 527
Tensile Strain, break, 50 mm/min	> 50	%	ISO 527
Tensile Modulus, 1 mm/min	2520	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	93	MPa	ISO 178
Flexural Modulus, 2 mm/min	2510	MPa	ISO 178
IMPACT			
Izod Impact, notched 80*10*4 +23°C	17	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 0°C	12	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	9	kJ/m ²	ISO 180/1A
THERMAL			
CTE, -30°C to 80°C, flow	6.9E-05	1/°C	ISO 11359-2
Ball Pressure Test, 75°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate A/50	111	°C	ISO 306
Vicat Softening Temp, Rate B/50	102	°C	ISO 306
Vicat Softening Temp, Rate B/120	104	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	99	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	88	°C	ISO 75/Ae
PHYSICAL			
Density	1.17	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.6	%	ISO 62





PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Moisture Absorption (23°C / 50% RH)	0.2	%	ISO 62
Melt Volume Rate, MVR at 260°C/2.16 kg	13	cm ³ /10 min	ISO 1133

DISCLAIMER

The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC as referred to herein means any legal entity belonging to the group of companies headed by Saudi Arabia Basic Industries Corporation.

