

GELOY™ RESIN XP4034

REGION ASIA

DESCRIPTION

PC/ASA. Excellent weatherability.

TYPICAL PROPERTY VALUES

Revision 20170816

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	62	MPa	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	25	%	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	88	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2510	MPa	ASTM D 790
Hardness, Rockwell R	110	-	ASTM D 785
IMPACT			
Izod Impact, notched, 23°C	320	J/m	ASTM D 256
Izod Impact, notched, -30°C	80	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	47	J	ASTM D 3763
Instrumented Impact Total Energy, -30°C	30	J	ASTM D 3763
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	115	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	104	°C	ASTM D 648
CTE, -20°C to 150°C, flow	7.2E-05	1/°C	ASTM E 831
CTE, -20°C to 150°C, xflow	7.2E-05	1/°C	ASTM E 831
Thermal Conductivity	0.25	W/m-°C	ASTM C177
PHYSICAL			
Specific Gravity	1.15	-	ASTM D 792
Water Absorption, 24 hours	0.25	%	ASTM D 570
Mold Shrinkage, flow, 3.2 mm (5)	0.5 – 0.7	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm (5)	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 280°C/3.8 kgf	24	g/10 min	ASTM D 1238
OPTICAL			
Gloss, untextured, 60 degrees	94	-	ASTM D 523
INJECTION MOLDING			
Drying Temperature	95 – 105	°C	
Drying Time	3 – 4	hrs	



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Drying Time (Cumulative)	8	hrs	
Maximum Moisture Content	0.04	%	
Melt Temperature	260 – 275	°C	
Nozzle Temperature	245 – 265	°C	
Front - Zone 3 Temperature	250 – 265	°C	
Middle - Zone 2 Temperature	245 – 260	°C	
Rear - Zone 1 Temperature	240 – 255	°C	
Mold Temperature	55 – 70	°C	
Back Pressure	0.3 – 1	MPa	
Screw Speed	30 – 80	rpm	
Shot to Cylinder Size	40 – 80	%	
Vent Depth	0.038 – 0.076	mm	
SHEET EXTRUSION			
Drying Temperature	90 – 100	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	8	hrs	
Minimum Moisture Content	0.04	%	
Melt Temperature	260 – 280	°C	
Barrel - Zone 1 Temperature	225 – 240	°C	
Barrel - Zone 2 Temperature	240 – 250	°C	
Barrel - Zone 3 Temperature	250 – 260	°C	
Barrel - Zone 4 Temperature	260 – 270	°C	
Adapter Temperature	260 – 270	°C	
Die Temperature	260 – 270	°C	
Roll Stack Temp - Top	100 – 120	°C	
Roll Stack Temp - Middle	95 – 110	°C	
Roll Stack Temp - Bottom	75 – 90	°C	

DISCLAIMER

The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC as referred to herein means any legal entity belonging to the group of companies headed by Saudi Arabia Basic Industries Corporation.

