



## CYCOLOY™ Resin CY5120

### Asia Pacific: COMMERCIAL

Non-chlorinated and non-brominated flame retardant PC/ABS offering balanced flow and impact for various applications.

TYPICAL PROPERTIES <sup>1</sup>	TYPICAL VALUE	Unit	Standard
<b>MECHANICAL</b>			
Tensile Stress, yld, Type I, 50 mm/min	610	kgf/cm <sup>2</sup>	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	4	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	40	%	ASTM D 638
Tensile Modulus, 50 mm/min	24700	kgf/cm <sup>2</sup>	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	950	kgf/cm <sup>2</sup>	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	24700	kgf/cm <sup>2</sup>	ASTM D 790
<b>IMPACT</b>			
Izod Impact, notched, 23°C	50	cm-kgf/cm	ASTM D 256
<b>THERMAL</b>			
HDT, 1.82 MPa, 6.4 mm, unannealed	80	°C	ASTM D 648
<b>PHYSICAL</b>			
Specific Gravity	1.2	-	ASTM D 792
Melt Flow Rate, 260°C/2.16 kgf	21	g/10 min	ASTM D 1238
<b>FLAME CHARACTERISTICS</b>			
UL Recognized, 94V-0 Flame Class Rating (3)	1.2	mm	UL 94
UL Recognized, 94-5VB Rating (3)	2	mm	UL 94

(1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.

(2) Only typical data for selection purposes. Not to be used for part or tool design.

(3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

(4) Internal measurements according to UL standards.

(5) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(6) Needs hard coat to consistently pass 60 sec Vertical Burn.

Source GMD, last updated:





**CYCOLOY™ Resin CY5120**  
**Asia Pacific: COMMERCIAL**

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
<b>Injection Molding</b>		
Drying Temperature	75 - 80	°C
Drying Time	3 - 4	hrs
Drying Time (Cumulative)	8	hrs
Maximum Moisture Content	0.04	%
Melt Temperature	230 - 275	°C
Nozzle Temperature	230 - 275	°C
Front - Zone 3 Temperature	225 - 275	°C
Middle - Zone 2 Temperature	215 - 260	°C
Rear - Zone 1 Temperature	210 - 255	°C
Mold Temperature	50 - 70	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	40 - 70	rpm
Shot to Cylinder Size	30 - 80	%
Vent Depth	0.038 - 0.076	mm

• NOTE: Back Pressure, Screw Speed, Shot to Cylinder Size and Vent Depth are only mentioned as general guidelines. These may not apply or need adjustment in specific situations such as low shot sizes, thin wall molding and gas-assist molding.

(1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.

(2) Only typical data for selection purposes. Not to be used for part or tool design.  
(3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.  
(4) Internal measurements according to UL standards.  
(5) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.  
(6) Needs hard coat to consistently pass 60 sec Vertical Burn.

Source GMD, last updated:

