



LNP™ VERTON™ Compound NV008E
Americas: COMMERCIAL

Also known as: LNP™ VERTON™ Compound PCA-F-7008 EM
Product reorder name: NV008E

LNP VERTON NV008E is a compound based on PC+ABS resin containing 40% Long Glass Fiber. Added features of this material include: Easy Molding. Structural.

TYPICAL PROPERTIES¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yield	1490	kgf/cm²	ASTM D 638
Tensile Stress, break	1490	kgf/cm²	ASTM D 638
Tensile Strain, yield	1.4	%	ASTM D 638
Tensile Strain, break	1.4	%	ASTM D 638
Tensile Modulus, 50 mm/min	206600	kgf/cm²	ASTM D 638
Flexural Stress	2170	kgf/cm²	ASTM D 790
Flexural Modulus	112400	kgf/cm²	ASTM D 790
Tensile Stress, yield	156	MPa	ISO 527
Tensile Stress, break	156	MPa	ISO 527
Tensile Strain, yield	1.3	%	ISO 527
Tensile Strain, break	1.3	%	ISO 527
Tensile Modulus, 1 mm/min	12400	MPa	ISO 527
Flexural Stress	224	MPa	ISO 178
Flexural Modulus	11700	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	75	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	31	cm-kgf/cm	ASTM D 256
Izod Impact, notched, -40°C	32	cm-kgf/cm	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	143	cm-kgf	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	50	kJ/m²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	28	kJ/m²	ISO 180/1A
Izod Impact, notched 80*10*4 -40°C	34	kJ/m²	ISO 180/1A

(1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.

Source GMD, last updated:

(2) Only typical data for selection purposes. Not to be used for part or tool design.
(3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.
(4) Internal measurements according to UL standards.
(5) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
(6) Needs hard coat to consistently pass 60 sec Vertical Burn.





LNP™ VERTON™ Compound NV008E
Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
CTE, -40°C to 40°C, flow	1.98E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	4.32E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	2.06E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	4.47E-05	1/°C	ISO 11359-2
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	131	°C	ISO 75/Af
PHYSICAL			
Density	1.49	g/cm³	ASTM D 792
Mold Shrinkage, xflow, 24 hrs (5)	0.3	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs (5)	0.05	%	ISO 294
Mold Shrinkage, xflow, 24 hrs (5)	0.27	%	ISO 294
Density	1.5	g/cm³	ISO 1183

(1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.

(2) Only typical data for selection purposes. Not to be used for part or tool design.
(3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.
(4) Internal measurements according to UL standards.
(5) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
(6) Needs hard coat to consistently pass 60 sec Vertical Burn.

Source GMD, last updated:





LNP™ VERTON™ Compound NV008E

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80 - 95	°C
Drying Time	2 - 4	hrs
Maximum Moisture Content	0.04	%
Melt Temperature	275 - 290	°C
Front - Zone 3 Temperature	280 - 295	°C
Middle - Zone 2 Temperature	270 - 280	°C
Rear - Zone 1 Temperature	260 - 270	°C
Mold Temperature	60 - 95	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm

(1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.

(2) Only typical data for selection purposes. Not to be used for part or tool design.

(3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

(4) Internal measurements according to UL standards.

(5) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(6) Needs hard coat to consistently pass 60 sec Vertical Burn.

Source GMD, last updated:

