



## LNP™ THERMOCOMP™ Compound NX10302

### Asia Pacific: COMMERCIAL

This is a PC/ABS compound with improved plating, surface and mechanical performance, a good candidate for Laser Direct Structuring applications.

| TYPICAL PROPERTIES <sup>1</sup>              | TYPICAL VALUE | Unit                    | Standard    |
|--|---------------|-------------------------|-------------|
| <b>MECHANICAL</b>                            |               |                         |             |
| Tensile Stress, yld, Type I, 5 mm/min        | 460           | kgf/cm <sup>2</sup>     | ASTM D 638  |
| Tensile Stress, brk, Type I, 5 mm/min        | 470           | kgf/cm <sup>2</sup>     | ASTM D 638  |
| Tensile Strain, yld, Type I, 5 mm/min        | 4.2           | %                       | ASTM D 638  |
| Tensile Strain, brk, Type I, 5 mm/min        | 100           | %                       | ASTM D 638  |
| Tensile Modulus, 50 mm/min                   | 25200         | kgf/cm <sup>2</sup>     | ASTM D 638  |
| Flexural Stress, yld, 1.3 mm/min, 50 mm span | 810           | kgf/cm <sup>2</sup>     | ASTM D 790  |
| Flexural Stress, brk, 1.3 mm/min, 50 mm span | 800           | kgf/cm <sup>2</sup>     | ASTM D 790  |
| Flexural Modulus, 1.3 mm/min, 50 mm span     | 24400         | kgf/cm <sup>2</sup>     | ASTM D 790  |
| <b>IMPACT</b>                                |               |                         |             |
| Izod Impact, unnotched, 23°C                 | NB            | cm-kgf/cm               | ASTM D 4812 |
| Izod Impact, notched, 23°C                   | 61            | cm-kgf/cm               | ASTM D 256  |
| <b>THERMAL</b>                               |               |                         |             |
| HDT, 1.82 MPa, 3.2mm, unannealed             | 108           | °C                      | ASTM D 648  |
| CTE, -40°C to 40°C, flow                     | 8.47E-05      | 1/°C                    | ASTM E 831  |
| CTE, -40°C to 40°C, xflow                    | 9.1E-05       | 1/°C                    | ASTM E 831  |
| <b>PHYSICAL</b>                              |               |                         |             |
| Density                                      | 1.26          | g/cm <sup>3</sup>       | ASTM D 792  |
| Water Absorption, 24 hours                   | 0.01          | %                       | ASTM D 570  |
| Moisture Absorption, 50% RH, 24 hrs          | 0.02          | %                       | ASTM D 570  |
| Mold Shrinkage, flow, 24 hrs (5)             | 0.6 - 0.65    | %                       | ASTM D 955  |
| Mold Shrinkage, xflow, 24 hrs (5)            | 0.5 - 0.56    | %                       | ASTM D 955  |
| Melt Volume Rate, MVR at 260°C/5.0 kg        | 14            | cm <sup>3</sup> /10 min | ISO 1133    |
| <b>ELECTRICAL</b>                            |               |                         |             |
| Relative Permittivity, 1 GHz                 | 2.74          | -                       | IEC 60250   |
| Dissipation Factor, 1 GHz                    | 0.003         | -                       | IEC 60250   |

(1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.

(2) Only typical data for selection purposes. Not to be used for part or tool design.  
(3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

(4) Internal measurements according to UL standards.

(5) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(6) Needs hard coat to consistently pass 60 sec Vertical Burn.

Source GMD, last updated:





## LNP™ THERMOCOMP™ Compound NX10302

### Asia Pacific: COMMERCIAL

| PROCESSING PARAMETERS       | TYPICAL VALUE | Unit |
|-----------------------------|---------------|------|
| <b>Injection Molding</b>    |               |      |
| Drying Temperature          | 85 - 100      | °C   |
| Drying Time                 | 6 - 8         | hrs  |
| Melt Temperature            | 250 - 290     | °C   |
| Nozzle Temperature          | 250 - 290     | °C   |
| Front - Zone 3 Temperature  | 250 - 280     | °C   |
| Middle - Zone 2 Temperature | 250 - 270     | °C   |
| Rear - Zone 1 Temperature   | 250 - 270     | °C   |
| Mold Temperature            | 60 - 90       | °C   |
| Back Pressure               | 0.3 - 0.7     | MPa  |
| Screw Speed                 | 40 - 70       | rpm  |

(1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.

(2) Only typical data for selection purposes. Not to be used for part or tool design.

(3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

(4) Internal measurements according to UL standards.

(5) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(6) Needs hard coat to consistently pass 60 sec Vertical Burn.

Source GMD, last updated:

