



Xenoy* Resin 1731J

Americas: COMMERCIAL

PBT+PC, Impact/chemical resistant. UV-Stabilized. Excellent physical property retention in automotive exteriors and OVAD.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	60	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	60	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	5.6	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	108	%	ASTM D 638
Tensile Strain, brk, Type I, 10 mm/min	240	%	SABIC - Japan Method
Tensile Modulus, 5 mm/min	2370	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	93	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2120	MPa	ASTM D 790
Tensile Stress, yield, 50 mm/min	60	MPa	ISO 527
Tensile Stress, break, 50 mm/min	57	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	5	%	ISO 527
Tensile Strain, break, 50 mm/min	104	%	ISO 527
Tensile Modulus, 1 mm/min	2370	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	92	MPa	ISO 178
Flexural Modulus, 2 mm/min	2210	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	814	J/m	ASTM D 256
Izod Impact, notched, -30°C	176	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	58	J	ASTM D 3763
Izod Impact, notched 80*10*4 +23°C	59	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	16	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	65	kJ/m ²	ISO 179/1eA

1) Typical values only. Variations within normal tolerances are possible for various colours. All values are measured at least after 48 hours storage at 23°C/50% relative humidity.
All properties, except the melt volume rate are measured on injection moulded samples.
All samples are prepared according to ISO 294.

2) Only typical data for material selection purpose. Not to be used for part or tool design.
3) This rating is not intended to reflect hazards presented this or any other material under actual fire conditions.
4) Own measurement according to UL.





Xenoy* Resin 1731J

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
IMPACT			
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	13	kJ/m ²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	130	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	110	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	92	°C	ASTM D 648
HDT, 0.45 MPa, 6.4 mm, unannealed	120	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	105	°C	ASTM D 648
CTE, -40°C to 40°C, flow	8.32E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	8.35E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	8.32E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	8.35E-05	1/°C	ISO 11359-2
Ball Pressure Test, 75°C +/- 2°C	PASS	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	130	°C	ISO 306
Vicat Softening Temp, Rate B/120	131	°C	ISO 306
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	116	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	98	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.22	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.65 - 0.73	%	SABIC Method
Melt Flow Rate, 250°C/5.0 kgf	9.6	g/10 min	ASTM D 1238
Density	1.22	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.28	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.08	%	ISO 62
Melt Volume Rate, MVR at 250°C/5.0 kg	8	cm ³ /10 min	ISO 1133

1) Typical values only. Variations within normal tolerances are possible for various colours. All values are measured at least after 48 hours storage at 23°C/50% relative humidity.
All properties, except the melt volume rate are measured on injection moulded samples.
All samples are prepared according to ISO 294.

2) Only typical data for material selection purpose. Not to be used for part or tool design.
3) This rating is not intended to reflect hazards presented this or any other material under actual fire conditions.
4) Own measurement according to UL.





Xenoy* Resin 1731J
Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	UNIT
Injection Molding		
Drying Temperature	110	°C
Drying Time	4 - 6	hrs
Drying Time (Cumulative)	8	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	260 - 275	°C
Nozzle Temperature	255 - 270	°C
Front - Zone 3 Temperature	255 - 275	°C
Middle - Zone 2 Temperature	250 - 270	°C
Rear - Zone 1 Temperature	245 - 265	°C
Mold Temperature	65 - 90	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	50 - 80	rpm
Shot to Cylinder Size	50 - 80	%
Vent Depth	0.013 - 0.02	mm

1) Typical values only. Variations within normal tolerances are possible for various colours. All values are measured at least after 48 hours storage at 23°C/50% relative humidity.
All properties, except the melt volume rate are measured on injection moulded samples.
All samples are prepared according to ISO 294.

2) Only typical data for material selection purpose. Not to be used for part or tool design.
3) This rating is not intended to reflect hazards presented this or any other material under actual fire conditions.
4) Own measurement according to UL.

Source, GMD, Last Update: 07/11/2005

