



Xenoy* Resin 5230R

Americas: COMMERCIAL

Unreinforced PBT+PC alloy. Excellent impact/chemical resistance and dimensional stability. Internal mold release.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	54	MPa	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	110	%	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	85	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2130	MPa	ASTM D 790
IMPACT			
Izod Impact, notched, 23°C	640	J/m	ASTM D 256
Izod Impact, notched, -30°C	213	J/m	ASTM D 256
Izod Impact, notched, -40°C	170	J/m	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	50	J	ASTM D 3763
Instrumented Impact Energy @ peak, -40°C	56	J	ASTM D 3763
THERMAL			
HDT, 0.45 MPa, 6.4 mm, unannealed	115	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	96	°C	ASTM D 648
Relative Temp Index, Elec	75	°C	UL 746B
Relative Temp Index, Mech w/impact	75	°C	UL 746B
Relative Temp Index, Mech w/o impact	75	°C	UL 746B
PHYSICAL			
Specific Gravity	1.22	-	ASTM D 792
Specific Volume	0.82	cm³/g	ASTM D 792
Water Absorption, 24 hours	0.12	%	ASTM D 570
Mold Shrinkage, flow, 3.2 mm	0.6 - 0.9	%	SABIC Method
ELECTRICAL			
Volume Resistivity	5.3E+16	Ohm-cm	ASTM D 257
Dielectric Strength, in air, 1.6 mm	27.9	kV/mm	ASTM D 149
Dielectric Strength, in air, 3.2 mm	18.3	kV/mm	ASTM D 149

1) Typical values only. Variations within normal tolerances are possible for various colours. All values are measured at least after 48 hours storage at 23°C/50% relative humidity.
All properties, except the melt volume rate are measured on injection moulded samples.
All samples are prepared according to ISO 294.

2) Only typical data for material selection purpose. Not to be used for part or tool design.
3) This rating is not intended to reflect hazards presented this or any other material under actual fire conditions.
4) Own measurement according to UL.





Xenoy* Resin 5230R

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
ELECTRICAL			
Relative Permittivity, 100 Hz	3.04	-	ASTM D 150
Relative Permittivity, 1 MHz	3.14	-	ASTM D 150
Dissipation Factor, 100 Hz	0.002	-	ASTM D 150
Dissipation Factor, 1 MHz	0.03	-	ASTM D 150
FLAME CHARACTERISTICS			
UL Recognized, 94HB Flame Class Rating (3)	1.49	mm	UL 94

1) Typical values only. Variations within normal tolerances are possible for various colours. All values are measured at least after 48 hours storage at 23°C/50% relative humidity.
All properties, except the melt volume rate are measured on injection moulded samples.
All samples are prepared according to ISO 294.

2) Only typical data for material selection purpose. Not to be used for part or tool design.
3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.
4) Own measurement according to UL.





Xenoy* Resin 5230R
Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	UNIT
Injection Molding		
Drying Temperature	110	°C
Drying Time	4 - 6	hrs
Drying Time (Cumulative)	8	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	260 - 275	°C
Nozzle Temperature	255 - 270	°C
Front - Zone 3 Temperature	255 - 275	°C
Middle - Zone 2 Temperature	250 - 270	°C
Rear - Zone 1 Temperature	245 - 265	°C
Mold Temperature	65 - 90	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	50 - 80	rpm
Shot to Cylinder Size	50 - 80	%
Vent Depth	0.013 - 0.02	mm

1) Typical values only. Variations within normal tolerances are possible for variose colours.All values are measured at least after 48 hours storage at 230C/50% relative humidity.
All properties, except the melt volume rate are measured on injection moulded samples.
All samples are prepared according to ISO 294.

2) Only typical data for material selection purpose.Not to be used for part or tool design.
3) This rating is not intended to reflect hazards presented this or any other material under actual fire conditions.
4) Own measurement according to UL.

Source, GMD, Last Update:10/31/2000

