



Xenoy* Resin 6620

Americas: COMMERCIAL

Unreinforced, impact modified thermoplastic alloy. Outstanding impact resistance particularly at low temperature

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	43	MPa	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	175	%	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	64	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	1720	MPa	ASTM D 790
Hardness, Rockwell R	108	-	ASTM D 785
IMPACT			
Izod Impact, unnotched, 23°C	1602	J/m	ASTM D 4812
Izod Impact, notched, 23°C	801	J/m	ASTM D 256
Izod Impact, notched, -40°C	640	J/m	ASTM D 256
Gardner, 23°C	54	J	ASTM D 3029
Modified Gardner, 23°C	54	J	ASTM D 3029
THERMAL			
HDT, 0.45 MPa, 6.4 mm, unannealed	98	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	60	°C	ASTM D 648
CTE, -40°C to 40°C, flow	5.04E-05	1/°C	ASTM E 831
CTE, 60°C to 138°C, flow	1.03E-04	1/°C	ASTM E 831
Relative Temp Index, Elec	75	°C	UL 746B
Relative Temp Index, Mech w/impact	75	°C	UL 746B
Relative Temp Index, Mech w/o impact	75	°C	UL 746B
PHYSICAL			
Specific Gravity	1.2	-	ASTM D 792
Specific Volume	0.83	cm ³ /g	ASTM D 792
Water Absorption, 24 hours	0.08	%	ASTM D 570
Mold Shrinkage, flow, 3.2 mm	1.6 - 1.8	%	SABIC Method

1) Typical values only. Variations within normal tolerances are possible for various colours. All values are measured at least after 48 hours storage at 23°C/50% relative humidity.
All properties, except the melt volume rate are measured on injection moulded samples.
All samples are prepared according to ISO 294.

2) Only typical data for material selection purpose. Not to be used for part or tool design.
3) This rating is not intended to reflect hazards presented this or any other material under actual fire conditions.
4) Own measurement according to UL.





Xenoy* Resin 6620

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
PHYSICAL			
Mold Shrinkage, xflow, 3.2 mm	1.6 - 1.8	%	SABIC Method
ELECTRICAL			
Volume Resistivity	5.5E+16	Ohm-cm	ASTM D 257
Dielectric Strength, in air, 3.2 mm	19	kV/mm	ASTM D 149
Dielectric Strength, in oil, 1.6 mm	27.9	kV/mm	ASTM D 149
Dielectric Strength, in oil, 3.2 mm	19	kV/mm	ASTM D 149
Relative Permittivity, 100 Hz	3.1	-	ASTM D 150
Relative Permittivity, 100 kHz	3	-	ASTM D 150
Relative Permittivity, 1 MHz	3	-	ASTM D 150
Dissipation Factor, 100 Hz	0.002	-	ASTM D 150
Dissipation Factor, 100 kHz	0.02	-	ASTM D 150
Dissipation Factor, 1 MHz	0.02	-	ASTM D 150
Arc Resistance, Tungsten {PLC}	5	PLC Code	ASTM D 495
Hot Wire Ignition {PLC}	3	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	1	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	0	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	0	PLC Code	UL 746A
FLAME CHARACTERISTICS			
UL Recognized, 94HB Flame Class Rating (3)	1.47	mm	UL 94

1) Typical values only. Variations within normal tolerances are possible for various colours. All values are measured at least after 48 hours storage at 23°C/50% relative humidity.
All properties, except the melt volume rate are measured on injection moulded samples.
All samples are prepared according to ISO 294.

2) Only typical data for material selection purpose. Not to be used for part or tool design.
3) This rating is not intended to reflect hazards presented this or any other material under actual fire conditions.
4) Own measurement according to UL.





Xenoy* Resin 6620

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	UNIT
Injection Molding		
Drying Temperature	105 - 115	°C
Drying Time	2 - 4	hrs
Drying Time (Cumulative)	6	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	240 - 260	°C
Nozzle Temperature	240 - 260	°C
Front - Zone 3 Temperature	240 - 260	°C
Middle - Zone 2 Temperature	230 - 250	°C
Rear - Zone 1 Temperature	225 - 245	°C
Mold Temperature	50 - 80	°C
Back Pressure	0.2 - 0.3	MPa
Shot to Cylinder Size	50 - 80	%
Vent Depth	0.013 - 0.02	mm

1) Typical values only. Variations within normal tolerances are possible for variose colours.All values are measured at least after 48 hours storage at 23OC/50% relative humidity.
All properties, expect the melt volume rate are measured on injection moulded samples.
All samples are prepared according to ISO 294.

2) Only typical data for material selection purpose.Not to be used for part or tool design.
3) This rating is not intended to reflect hazards presented this or any other material under actual fire conditions.
4) Own measurement according to UL.

Source, GMD, Last Update:10/31/2000

