



Xenoy* Resin ECX101
Asia Pacific: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
MECHANICAL			
Tensile Stress, yield	65	MPa	SABIC - Japan Method
Tensile Strain, break	300 - 300	%	SABIC - Japan Method
Flexural Stress	100	MPa	ASTM D 790
Flexural Modulus	2500	MPa	ASTM D 790
IMPACT			
Izod Impact, notched, 23°C	67	J/m	ASTM D 256
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	118	°C	ASTM D 648
PHYSICAL			
Specific Gravity	1.22	-	ASTM D 792

1) Typical values only. Variations within normal tolerances are possible for various colours. All values are measured at least after 48 hours storage at 230C/50% relative humidity.
All properties, except the melt volume rate are measured on injection moulded samples.
All samples are prepared according to ISO 294.

2) Only typical data for material selection purpose. Not to be used for part or tool design.
3) This rating is not intended to reflect hazards presented this or any other material under actual fire conditions.
4) Own measurement according to UL.

