



Xenoy* Resin X3108UV

Americas: COMMERCIAL

Unreinforced, UV-stabilized, flame retardant, impact modified PBT+PC with V0 at 0.8mm thickness. For applications like wall switches and enclosures.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	52	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	42	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	6	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	26	%	ASTM D 638
Tensile Modulus, 5 mm/min	2150	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	78	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2020	MPa	ASTM D 790
Tensile Stress, yield, 50 mm/min	50	MPa	ISO 527
Tensile Stress, break, 50 mm/min	40	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	5	%	ISO 527
Tensile Strain, break, 50 mm/min	30	%	ISO 527
Tensile Modulus, 1 mm/min	2200	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	80	MPa	ISO 178
Flexural Modulus, 2 mm/min	2000	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	522	J/m	ASTM D 256
Izod Impact, notched, -30°C	158	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	60	J	ASTM D 3763
Izod Impact, notched 80*10*4 +23°C	45	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	10	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	45	kJ/m ²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	148	°C	ASTM D 1525

1) Typical values only. Variations within normal tolerances are possible for various colours. All values are measured at least after 48 hours storage at 23°C/50% relative humidity.
All properties, except the melt volume rate are measured on injection moulded samples.
All samples are prepared according to ISO 294.

2) Only typical data for material selection purpose. Not to be used for part or tool design.
3) This rating is not intended to reflect hazards presented this or any other material under actual fire conditions.
4) Own measurement according to UL.





Xenoy* Resin X3108UV

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	88	°C	ASTM D 648
CTE, -40°C to 40°C, flow	9.E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	9.E-05	1/°C	ASTM E 831
CTE, 23°C to 80°C, flow	1.E-04	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	1.E-04	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	pass	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	145	°C	ISO 306
Vicat Softening Temp, Rate B/120	150	°C	ISO 306
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	85	°C	ISO 75/Ae
Relative Temp Index, Elec	120	°C	UL 746B
Relative Temp Index, Mech w/impact	120	°C	UL 746B
Relative Temp Index, Mech w/o impact	140	°C	UL 746B
PHYSICAL			
Specific Gravity	1.34	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	1.1 - 1.2	%	SABIC Method
Melt Flow Rate, 250°C/5.0 kgf	9.3	g/10 min	ASTM D 1238
Density	1.34	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.5	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.15	%	ISO 62
Melt Volume Rate, MVR at 250°C/5.0 kg	8	cm ³ /10 min	ISO 1133
ELECTRICAL			
Volume Resistivity	1.E+16	Ohm-cm	ASTM D 257
Surface Resistivity	1.E+16	Ohm	ASTM D 257
Volume Resistivity	>1.E+15	Ohm-cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ohm	IEC 60093

1) Typical values only. Variations within normal tolerances are possible for various colours. All values are measured at least after 48 hours storage at 23°C/50% relative humidity.
All properties, except the melt volume rate are measured on injection moulded samples.
All samples are prepared according to ISO 294.

2) Only typical data for material selection purpose. Not to be used for part or tool design.
3) This rating is not intended to reflect hazards presented this or any other material under actual fire conditions.
4) Own measurement according to UL.





Xenoy* Resin X3108UV
Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
ELECTRICAL			
Dielectric Strength, in oil, 3.2 mm	18	kV/mm	IEC 60243-1
Relative Permittivity, 50/60 Hz	3	-	IEC 60250
Relative Permittivity, 1 MHz	2.9	-	IEC 60250
Dissipation Factor, 50/60 Hz	0.002	-	IEC 60250
Dissipation Factor, 1 MHz	0.007	-	IEC 60250
Comparative Tracking Index	225	V	IEC 60112
FLAME CHARACTERISTICS			
UL Compliant, 94V-0 Flame Class Rating (3)(4)	0.75	mm	UL 94 by GE
UL Compliant, 94-5VA Rating (3)(4)	2.5	mm	UL 94 by GE
Glow Wire Flammability Index 960°C, passes at	1	mm	IEC 60695-2-12
Oxygen Index (LOI)	30	%	ISO 4589

1) Typical values only. Variations within normal tolerances are possible for variose colours.All values are measured at least after 48 hours storage at 230C/50% relative humidity.
All properties, expect the melt volume rate are measured on injection moulded samples.
All samples are prepared according to ISO 294.

2) Only typical data for material selection purpose.Not to be used for part or tool design.
3) This rating is not intended to reflect hazards presented this or any other material under actual fire conditions.
4) Own measurement according to UL.

Source, GMD, Last Update:11/06/2006





Xenoy* Resin X3108UV
Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	UNIT
Injection Molding		
Drying Temperature	110 - 120	°C
Drying Time	2 - 4	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	250 - 270	°C
Nozzle Temperature	240 - 260	°C
Front - Zone 3 Temperature	245 - 265	°C
Middle - Zone 2 Temperature	240 - 255	°C
Rear - Zone 1 Temperature	230 - 245	°C
Hopper Temperature	40 - 60	°C
Mold Temperature	40 - 100	°C

1) Typical values only. Variations within normal tolerances are possible for variose colours.All values are measured at least after 48 hours storage at 23OC/50% relative humidity.
All properties, except the melt volume rate are measured on injection moulded samples.
All samples are prepared according to ISO 294.

2) Only typical data for material selection purpose.Not to be used for part or tool design.
3) This rating is not intended to reflect hazards presented this or any other material under actual fire conditions.
4) Own measurement according to UL.

Source, GMD, Last Update:11/06/2006

