

# XENOV™ RESIN X5230

REGION EUROPE

## DESCRIPTION

Mineral filled PC/PET blend with high flow, high heat, dimensional stability, low shrinkage and low CTE, especially for painted applications

## TYPICAL PROPERTY VALUES

Revision 20170816

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, yield, 5 mm/min	58	MPa	ISO 527
Tensile Stress, break, 5 mm/min	42	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	3.6	%	ISO 527
Tensile Strain, break, 5 mm/min	9	%	ISO 527
Tensile Modulus, 1 mm/min	3850	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	95	MPa	ISO 178
Flexural Modulus, 2 mm/min	3750	MPa	ISO 178
<b>IMPACT</b>			
Izod Impact, unnotched 80*10*4 +23°C	137	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	120	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	10	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	7	kJ/m <sup>2</sup>	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	10	kJ/m <sup>2</sup>	ISO 179/1eA
<b>THERMAL</b>			
CTE, -30°C to 80°C, flow	5.4E-05	1/°C	ISO 11359-2
CTE, -30°C to 80°C, xflow	7.4E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	137	°C	ISO 306
Vicat Softening Temp, Rate B/120	140	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	109	°C	ISO 75/Af
<b>PHYSICAL</b>			
Mold Shrinkage on Tensile Bar, flow (2) (5)	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 265°C/5.0 kgf	28	g/10 min	ASTM D 1238
Density	1.33	g/cm <sup>3</sup>	ISO 1183
Water Absorption, (23°C/sat)	0.42	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.14	%	ISO 62
Melt Volume Rate, MVR at 265°C/5.0 kg	24	cm <sup>3</sup> /10 min	ISO 1133



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>INJECTION MOLDING</b>			
Drying Temperature	110 – 120	°C	
Drying Time	4 – 6	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	265 – 275	°C	
Nozzle Temperature	260 – 275	°C	
Front - Zone 3 Temperature	260 – 280	°C	
Middle - Zone 2 Temperature	250 – 275	°C	
Rear - Zone 1 Temperature	240 – 270	°C	
Hopper Temperature	60 – 80	°C	
Mold Temperature	60 – 100	°C	

## DISCLAIMER

The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC as referred to herein means any legal entity belonging to the group of companies headed by Saudi Arabia Basic Industries Corporation.

