

High Density Polyethylene FH35

Description:

FH35 resin is a High Density Polyethylene that is designed for flat die film extrusion and shows good mechanical properties.

Applications:

Diapers, sanitary napkins and other specialties.

Process:

Cast Film Extrusion

Control Properties:

control i ropertiesi			
	ASTM Methods	Units	Values
Melt Flow Rate (190/2.16)	D 1238	g/10 min	4.9
Density	D 792	g/cm³	0.942

Typical Properties:

Blown Film Properties^a

·	ASTM Methods	Units	Values
Tensile Strength at Break (MD/TD)	D 882	MPa	30/20
Elongation at Break (MD/TD)	D 882	%	1350/430
Flexural Modulus – 1% Secant (MD/TD)	D 882	MPa	490/540
Dart Drop Impact	D 1709	g/F50	ND
Elmendorf Tear Strength (MD/TD)	D 1922	gF	13/20

⁽a) 25 um Film Gauge, obtained in 40 mm extruder with blow up ratio of 2.2:1 (MD: Machine direction: TD: Transversal direction).

Recommended Processing Conditions:

The FH35 resin is indicated to be in cast die film extruders under processing conditions comparable to the other Linear Medium Density Polyethylenes of similar fluidity and density. The recommended temperature profile:

- Extrusion: 180 to 250°C.
- Die Head and Die: 250 to 290°C.

Final Remarks:

- This resin meets the requirements for olefin polymers as defined in 21 CFR, section 177.1520 issued by FDA Food and Drug Administration in force on the
- date of publication of this specification. The additives present are covered in appropriate regulation by FDA.

 2. These information reflect typical values obtained in our laboratories, but should not be considered as absolute or as warranted values. Only the properties and values mentioned on the Certificate of Quality are considered as guarantee of the product.
- In some applications, Braskem has developed tailor-made resins to reach specific requirements.
- In case of doubt regarding utilization, or for other applications, please contact our Application Engineering.

 For information about safety, handling, individual protection, first aids and waste disposal, please see MSDS. CAS Registry number: 25087-34-7..

 The mentioned values in this report can be changed at any moment without Braskem previous communication.
- Braskem does not recommend this grade for packages, parts or any kind of product manufacture that will be used for storage or contact with solution that will have internal contact with human body.

 8. The content of this Data Sheet replaces previous revisions published for this product.
- 9. This resin does not contain the substance Bisphenol A (BPA, CAS # No. 80-05-7) in its composition.



