# Low Density Polyethylene BF0323HC

#### **Description:**

BF0323HC is a high molecular weight grade produced under high pressure. Films obtained with this product show excellent mechanical and optical properties.

### **Applications:**

Heavy duty bags; agriculture, co extruded and shrink films.

#### Process:

Blown Film Extrusion; Blow Molding

### **Control Properties:**

	ASTM Method	Units	Values
Melt Flow Rate (190/2.16)	D 1238	g/10 min	0.32
Density	D 1505	g/cm3	0.923

## **Typical Properties:**

Blown Film Properties<sup>a</sup>

	ASTM Method	Units	Values
Tensile Strength at Break (MD/TD)	D 882	MPa	20/20
Elongation at Break (MD/TD)	D 882	%	390/930
Dart Drop Impact	D 1709	g/F50	290
Elmendorf Tear Strength (MD/TD)	D 1922	gF	NDb/270
Haze	D 1003	%	10
Gloss - Angle 60°	D 2457	%	92

(a) 70 µm Film Gauge, obtained in 75 mm extruder, with 2:1 BUR. die gap 1.0 mm, (MD: Machine direction; TD: Transversal direction). (b) ND: Not Determined

## **Final Remarks:**

- This resin meets the requirements for olefin polymers as defined in 21 CFR, section 177.1520 issued by FDA Food and Drug Administration in force on the date 1. of publication of this specification.
- The information presented in this Data Sheet reflects typical values obtained in our laboratories, but should not be considered as absolute or as warranted values. Only the properties and values mentioned on the Certificate of Quality are considered as guarantee of the product. In some applications, Braskem has developed tailor-made resins to reach specific requirements. 2
- In case of doubt regarding utilization, or for other applications, please contact our Technical Assistance
- For information about safety, handling, individual protection, first aids and waste disposal, please see MSDS. CAS Registry number: 9002-88-4. 5
- The mentioned values in this report can be changed at any moment without Braskem previous communication 6.
- Braskem does not recommend this grade for packages, parts or any kind of product manufacture that will be used for storage or contact with solution that will 7. have internal contact with human body.
- The content of this Data Sheet replaces previous revisions published for this product. This resin does not contain the substance Bisphenol A (BPA, CAS # No. 80-05-7) in its composition. 8



