

Linear Low Density Polyethylene ML3601U

Description:

The resin ML3601U is a Linear Low Density Polyethylene indicated for rotational molding.

Applications:

Large tanks
Water tanks
Tanks for chemical and agricultural products
Septic tanks and manholes

Technical Characteristics:

Good surface finishing
Excellent impact resistance
Creep Resistance
UV and heat stabilization

Additives:

Weathering resistance UV14 and antioxidants.

Resin Properties:

	Método ASTM	Unidades	Típicos
Melt Flow Rate (190/2.16)	D 1238	g/10 min	3.3
Density	D 1505	g/cm ³	0.939
Melting Temperature	D 3418	°C	127

Typical Properties ^a:

	Método ASTM	Unidades	Típicos
Tensile Strength at Yield	D 638	MPa	21
Tensile Elongation at Yield	D 638	%	14
Tensile Elongation at Break	D 638	%	> 1000
Flexural Modulus	D 790	MPa	760
Environmental Stress Cracking Resistance(ESCR) ^b : 10% Igepal 100% Igepal	D 1693	h/F50	145 > 1000
Heat Deflection Temperature: 0,455 MPa 1,82 MPa	D 648	°C	60 41
Impact Strength at -40°C: 3,17 mm thickness 6,34 mm thickness	ARM	J	82 228
OIT	D3895	Min.	>100

(a) Test specimens prepared from compression molded sheet made according to ASTM D 4703.

(b) Compression molded 2 mm thickness, 0.3 mm notched-plaques; 50°C.

(c) Rotomolded plaque.

Final Remarks:

1. This resin meets the requirements for olefin polymers as defined in 21 CFR, section 177.1520 issued by FDA – Food and Drug Administration in force on the date of publication of this specification. The additives present are covered in appropriate regulation by FDA
2. The information presented in this Data Sheet reflects typical values obtained in our laboratories, but should not be considered as absolute or as warranted values. Only the properties and values mentioned on the Certificate of Quality are considered as guarantee of the product.
3. In some applications, Braskem has developed tailor-made resins to reach specific requirements.
4. In case of doubt regarding utilization, or for other applications, please contact our Application Engineering.
5. For information about safety, handling, individual protection, first aids and waste disposal, please see MSDS. CAS Registry number: 25087-34-7.
6. The mentioned values in this report can be changed at any moment without Braskem previous communication.
7. Braskem does not recommend this grade for plastic containers of physiological saline and/or parenterally administered drugs.
8. The content of this Data Sheet replaces previous revisions published for this product.
9. This resin does not contain the substance Bisphenol A (BPA, CAS # No. 80-05-7) in its composition.