

# INSPIRE™ 364

聚对苯二甲酸丁二酯 + PC + PET

Braskem Europe GmbH

## Technical Data

### 产品说明

INSPIRE™ 364 Performance Polymer is a random copolymer for thin wall injection moulding applications. The grade is characterized by a balanced mix of key properties e.g. good stiffness/impact balance, superior organoleptics (low taste and odor), excellent optical properties and very high flowability.

### Application:

- Thin Wall Injection Moulding
- Housewares
- Media packaging
- Caps and closures

### Process:

- Thin Wall Injection Moulding

### 总览

特性	<ul style="list-style-type: none"><li>• Excellent Organoleptic Properties</li><li>• Low Halogen Content</li></ul>	<ul style="list-style-type: none"><li>• 光学性能</li><li>• 良好的流动性</li></ul>	<ul style="list-style-type: none"><li>• 良好刚性</li><li>• 良好抗撞击性</li></ul>
用途	<ul style="list-style-type: none"><li>• 包装</li><li>• 薄壁部件</li></ul>	<ul style="list-style-type: none"><li>• 护罩</li><li>• 媒介包装</li></ul>	<ul style="list-style-type: none"><li>• 外壳</li><li>• 医疗器材</li></ul>
机构评级	<ul style="list-style-type: none"><li>• FDA 21 CFR 177.1520(c) 3.1a</li><li>• 欧洲 No 10/2011</li></ul>		

物理性能	额定值 单位制	测试方法
密度	0.900 g/cm <sup>3</sup>	ISO 1183
熔流率 (熔体流动速率) (230°C/2.16 kg)	42 g/10 min	ISO 1133
机械性能	额定值 单位制	测试方法
拉伸应力 (屈服, 注塑)	28.0 MPa	ISO 527-2
拉伸应变 (屈服, 注塑)	12 %	ISO 527-2
弯曲模量 (注塑)	1050 MPa	ISO 178
冲击性能	额定值 单位制	测试方法
简支梁缺口冲击强度 0°C, 注塑	2.0 kJ/m <sup>2</sup>	ISO 179/1eA
23°C, 注塑	6.0 kJ/m <sup>2</sup>	
热性能	额定值 单位制	测试方法
热变形温度 <sup>3</sup> (0.45 MPa, 未退火)	83.0 °C	ISO 75-2/B
维卡软化温度 <sup>3</sup>	127 °C	ISO 306/A
光学性能	额定值 单位制	测试方法
雾度 (1000 µm, 注塑)	12.0 %	ASTM D1003

