

Braskem PP C715-12NHP

抗冲击共聚聚丙烯

Braskem Europe GmbH

Technical Data

产品说明

BRASKEM C715-12NHP Polypropylene Resin is an impact copolymer for various injection moulding applications. BRASKEM C715-12NHP Polypropylene Resin has a good balance of mechanical properties featuring high stiffness and excellent impact strength, also at low temperatures. BRASKEM C715-12NHP Polypropylene Resin is a medium flow impact copolymer exhibiting a higher rigidity impact balance than conventional impact copolymers at similar flow.

Applications:

- Containers, baskets, pails, caps & closures and other consumer applications
- General automotive

Process:

- Injection moulding

总览

特性	<ul style="list-style-type: none">• 抗冲共聚物• 良好刚性	<ul style="list-style-type: none">• 良好抗撞击性• 耐低温冲击	<ul style="list-style-type: none">• 中等流动性
用途	<ul style="list-style-type: none">• 护罩• 汽车领域的应用	<ul style="list-style-type: none">• 容器• 桶	<ul style="list-style-type: none">• 外壳• 消费品应用领域
机构评级	<ul style="list-style-type: none">• FDA FCN 843	<ul style="list-style-type: none">• 欧洲 No 10/2011	
加工方法	<ul style="list-style-type: none">• 注射成型		

物理性能	额定值	单位制	测试方法
密度	0.900	g/cm ³	ISO 1183
熔流率 (熔体流动速率) (230°C/2.16 kg)	12	g/10 min	ISO 1133
机械性能	额定值	单位制	测试方法
拉伸应力 (屈服, 注塑)	24.0	MPa	ISO 527-2
拉伸应变 (屈服, 注塑)	8.0	%	ISO 527-2
弯曲模量 (注塑)	1450	MPa	ISO 178
冲击性能	额定值	单位制	测试方法
简支梁缺口冲击强度			ISO 179/1eA
-20°C, 注塑	4.5	kJ/m ²	
0°C, 注塑	6.0	kJ/m ²	
23°C, 注塑	10	kJ/m ²	
热性能	额定值	单位制	测试方法
热变形温度 ⁴ (0.45 MPa, 未退火)	100	°C	ISO 75-2/B
维卡软化温度 ⁴	152	°C	ISO 306/A

