



CYCOLACTM RESIN INP338T

REGION AMERICAS

DESCRIPTION

ABS, powder, highest impact. FDA compliant (part use must be at room temperature or below).

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Hardness, Shore D	40	-	ASTM D 2240
PHYSICAL			
Specific Gravity	0.95	-	ASTM D 792
Density (Molded)	0.96	g/cm ³	ISO 1183
Mean Resin Particle Size	200	micrometer	SABIC method
Total NA Volatiles	0.2	%	SABIC method
BD	70	%	SABIC method
Bulk Density	0.25	g/cm ³	ASTM D 1895