



CYCOLACTM RESIN INP362

REGION AMERICAS

DESCRIPTION

ABS, powder, high impact. FDA compliant (part use must be at room temperature or below).

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Hardness, Shore D	44	-	ASTM D 2240
PHYSICAL			
Specific Gravity	0.97	-	ASTM D 792
Density	0.98	g/cm ³	ISO 1183
Mean Resin Particle Size	700	micrometer	SABIC method
Total NA Volatiles	0.1	%	SABIC method
Rubber	62	%	SABIC method
Bulk Density	0.29	g/cm ³	ASTM D 1895