



CYCOLACTM RESIN MG47U

REGION AMERICAS

DESCRIPTION

Improved UV performance, multi-purpose, injection molding ABS providing a favorable balance of engineering properties.

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Hardness, Rockwell R	112	-	ASTM D 785
Tensile Stress, yield, 50 mm/min	45	MPa	ISO 527
Tensile Stress, break, 50 mm/min	33	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	2.4	%	ISO 527
Tensile Strain, break, 50 mm/min	20	%	ISO 527
Tensile Modulus, 1 mm/min	2500	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	68	MPa	ISO 178
Flexural Modulus, 2 mm/min	2250	MPa	ISO 178
IMPACT			
Izod Impact, notched 80*10*4 +23°C	20	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	8	kJ/m ²	ISO 180/1A
THERMAL			
Vicat Softening Temp, Rate B/50	99	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	94	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	80	°C	ASTM D 648
CTE, -40°C to 40°C, flow	8.82E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	8.82E-05	1/°C	ASTM E 831
Vicat Softening Temp, Rate B/50	98	°C	ISO 306
Vicat Softening Temp, Rate B/120	100	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	81	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.04	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.8	%	SABIC method
Melt Viscosity, 240°C, 1000 sec-1	2250	Poise	ASTM D 3825
Density	1.04	g/cm ³	ISO 1183
Melt Flow Rate, 220°C/ 10.0 kg	17	g/10 min	ISO 1133
INJECTION MOLDING			
Drying Temperature	80 – 95	°C	
Drying Time	2 – 4	hrs	
Drying Time (Cumulative)	8	hrs	
Maximum Moisture Content	0.1	%	
Melt Temperature	220 – 260	°C	
Nozzle Temperature	220 – 260	°C	
Front - Zone 3 Temperature	215 – 240	°C	



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Middle - Zone 2 Temperature	205 – 225	°C	
Rear - Zone 1 Temperature	190 – 210	°C	
Mold Temperature	50 – 70	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	30 – 60	rpm	
Shot to Cylinder Size	50 – 70	%	
Vent Depth	0.038 – 0.051	mm	