



Cycolac* Resin GDT6400

Americas: COMMERCIAL

AUTOMOTIVE. Low gloss for unpainted interior applications. Available in custom colors.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	450	kgf/cm ²	ASTM D 638
Tensile Modulus, 5 mm/min	22400	kgf/cm ²	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	710	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	22400	kgf/cm ²	ASTM D 790
IMPACT			
Izod Impact, notched, 23°C	25	cm-kgf/cm	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	300	cm-kgf	ASTM D 3763
Instrumented Impact Energy @ peak, -30	117	cm-kgf	ASTM D 3763
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	92	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	78	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	83	°C	ASTM D 648
CTE, -40°C to 60°C, flow	1.55E-04	1/°C	ASTM E 831
Relative Temp Index, Elec	60	°C	UL 746B
Relative Temp Index, Mech w/impact	60	°C	UL 746B
Relative Temp Index, Mech w/o impact	60	°C	UL 746B
PHYSICAL			
Specific Gravity	1.05	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.5 - 0.8	%	GE Method
Melt Flow Rate, 220°C/10.0 kgf	16	g/10 min	ASTM D 1238
Melt Viscosity, 260°C, 1000 sec-1	1600	poise	ASTM D 3825
FLAME CHARACTERISTICS			
UL Recognized, 94HB Flame Class Rating (3)	1.49	mm	UL 94



Cycolac* Resin GDT6400

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	UNIT
Injection Molding		
Drying Temperature	80 - 90	°C
Drying Time	2 - 4	hrs
Drying Time (Cumulative)	8	hrs
Maximum Moisture Content	0.01	%
Melt Temperature	230 - 275	°C
Nozzle Temperature	230 - 275	°C
Front - Zone 3 Temperature	230 - 245	°C
Middle - Zone 2 Temperature	215 - 225	°C
Rear - Zone 1 Temperature	200 - 210	°C
Mold Temperature	25 - 60	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	30 - 60	rpm
Shot to Cylinder Size	50 - 70	%
Vent Depth	0.038 - 0.051	mm