



LNP™ STAT-LOY™ Compound A3000TXB

Americas: COMMERCIAL

Also known as: LNP™ STAT-LOY™ Compound A3000TXB

Product reorder name: A3000TXB

LNP STAT-LOY A3000TXB is a compound based on ABS resin. Added features of this material include: Antistatic, Transparent. Bioassessed to ISO 10993.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	380	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	270	kgf/cm ²	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	4	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	31	%	ASTM D 638
Tensile Modulus, 5 mm/min	16900	kgf/cm ²	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	550	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	16600	kgf/cm ²	ASTM D 790
Tensile Stress, yield, 5 mm/min	37	MPa	ISO 527
Tensile Stress, break, 5 mm/min	26	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	4	%	ISO 527
Tensile Strain, break, 5 mm/min	29	%	ISO 527
Tensile Modulus, 1 mm/min	1550	MPa	ISO 527
Flexural Stress	49	MPa	ISO 178
Flexural Modulus, 2 mm/min	1490	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	13	cm-kgf/cm	ASTM D 256
Multiaxial Impact	336	cm-kgf	ISO 6603
Instrumented Impact Total Energy, 23°C	203	cm-kgf	ASTM D 3763
Izod Impact, notched 80*10*4 +23°C	14	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	78	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	66	°C	ASTM D 648
CTE, -30°C to 30°C, flow	1.E-05	1/°C	ASTM D 696



LNP™ STAT-LOY™ Compound A3000TXB

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
CTE, -30°C to 30°C, xflow	1.09E-04	1/°C	ASTM D 696
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	77	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	66	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.09	-	ASTM D 792
Density	1.08	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.54	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.4 - 0.6	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.6 - 0.8	%	ASTM D 955
Moisture Absorption (23°C / 50% RH)	0.81	%	ISO 62
ELECTRICAL			
Volume Resistivity	1.E+10 - 1.E+12	Ohm-cm	ASTM D 257
Surface Resistivity	1.E+09 - 1.E+11	Ohm	ASTM D 257
Static Decay, 5000V to <50V	<1	< seconds	FTMS101B



LNP™ STAT-LOY™ Compound A3000TXB

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	70 - 80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.05 - 0.1	%
Melt Temperature	200 - 210	°C
Front - Zone 3 Temperature	205 - 215	°C
Middle - Zone 2 Temperature	195 - 205	°C
Rear - Zone 1 Temperature	180 - 195	°C
Mold Temperature	10 - 50	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm