



LNP™ THERMOCOMP™ Compound AW00A

Europe-Africa-Middle East: COMMERCIAL

LNP THERMOCOMP AW00A is a compound based on Acrylonitrile Butadiene Styrene resin containing Wollastonite.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yield, 5 mm/min	25	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	2.1	%	ISO 527
Tensile Modulus, 1 mm/min	3400	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	49	MPa	ISO 178
Flexural Stress, break, 2 mm/min	39	MPa	ISO 178
Flexural Strain, break, 2 mm/min	5.9	%	ISO 178
Flexural Modulus, 2 mm/min	3900	MPa	ISO 178
IMPACT			
Izod Impact, unnotched 80*10*4 +23°C	15	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	5	kJ/m ²	ISO 180/1A
THERMAL			
CTE, 23°C to 60°C, flow	6.9E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	9.3E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	95	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	81	°C	ISO 75/Af
PHYSICAL			
Mold Shrinkage, flow (5)	0.5	%	SABIC Method
Density	1.38	g/cm ³	ISO 1183
Water Absorption, 23°C/24hrs	0.24	%	ISO 62-1



LNP™ THERMOCOMP™ Compound AW00A

Europe-Africa-Middle East: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.05 - 0.1	%
Melt Temperature	260	°C
Front - Zone 3 Temperature	265 - 275	°C
Middle - Zone 2 Temperature	230 - 245	°C
Rear - Zone 1 Temperature	205 - 215	°C
Mold Temperature	70 - 80	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm