



# GELOY™ RESIN INP984

REGION AMERICAS

## DESCRIPTION

ASA powder

## TYPICAL PROPERTY VALUES

| PROPERTIES               | TYPICAL VALUES | UNITS             | TEST METHODS |
|--------------------------|----------------|-------------------|--------------|
| MECHANICAL               |                |                   |              |
| Hardness, Shore D        | 65             | -                 | ASTM D 2240  |
| PHYSICAL                 |                |                   |              |
| Specific Gravity         | 1.06           | -                 | ASTM D 792   |
| Density (Molded)         | 1.07           | g/cm <sup>3</sup> | ISO 1183     |
| Mean Resin Particle Size | 465            | micrometer        | SABIC method |
| Total NA Volatiles       | 0.1            | %                 | SABIC method |
| Rubber                   | 45             | %                 | SABIC method |
| Bulk Density             | 0.26           | g/cm <sup>3</sup> | ASTM D 1895  |