

LNP™ THERMOCOMP™ COMPOUND 2X95787

PDX-FP-E-95787

REGION ASIA

DESCRIPTION

LNP THERMOCOMP 2X95787 is a compound based on ETFE Copolymer resin containing Proprietary Filler(s).

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yield	48	MPa	ASTM D 638
Tensile Stress, break	45	MPa	ASTM D 638
Tensile Strain, yield	9.3	%	ASTM D 638
Tensile Strain, break	13.7	%	ASTM D 638
Tensile Modulus, 50 mm/min	42740	MPa	ASTM D 638
Tensile Stress, yield	47	MPa	ISO 527
Tensile Stress, break	45	MPa	ISO 527
Tensile Strain, yield	8.6	%	ISO 527
Tensile Strain, break	12.8	%	ISO 527
Tensile Modulus, 1 mm/min	4050	MPa	ISO 527
Flexural Stress	66	MPa	ISO 178
Flexural Modulus	4000	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	1335	J/m	ASTM D 4812
Izod Impact, notched, 23°C	480	J/m	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	19	J	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	83	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	24	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	222	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	107	°C	ASTM D 648
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	203	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	91	°C	ISO 75/Af

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Density	1.84	g/cm ³	ASTM D 792
Mold Shrinkage, flow, 24 hrs (5)	1.8	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	2.4	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs (5)	1.8	%	ISO 294
Mold Shrinkage, xflow, 24 hrs (5)	2.4	%	ISO 294
Density	1.83	g/cm ³	ISO 1183
MECHANICAL PROPERTIES			
Flexural modulus	33780	MPa	ISO 178/1A
INJECTION MOLDING			
Drying Temperature	120 – 150	°C	
Drying Time	4	hrs	
Melt Temperature	370 – 390	°C	
Front - Zone 3 Temperature	390 – 400	°C	
Middle - Zone 2 Temperature	355 – 365	°C	
Rear - Zone 1 Temperature	315 – 325	°C	
Mold Temperature	140 – 165	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	