

# SABIC® HDPE B4660

## HIGH DENSITY POLYETHYLENE

### DESCRIPTION

B4660 grade are medium molecular weight High Density Polyethylene homopolymer for blow molding Applications. They are primarily Designed for imparting high rigidity, toughness and good processability. These unique properties offer the possibility to reduce weight at very good top load strength. B4660: Suitable for Dairy products and Juice Packaging

### TYPICAL APPLICATIONS

B4660 Series resins are primarily intended for blow molding bottles for the food and beverage industry. The grade B4660AB is specifically recommended for water packaging applications. The grades are intended to meet customer specifications in respect of purity, healthiness and organoleptic. They can also be used in other hollow thin-walled parts and profile extrusions. They are not recommended for packaging Environmentally active materials such as soaps, detergents, shampoos, etc.

### TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES <sup>(1)</sup></b>			
<b>Melt Flow Rate (MFR)</b>			
@ 190°C & 2.16 kg load	0.7	g/10 min	ASTM D1243
@ 190°C & 5 kg load	2.8	g/10 min	ISO 1133
@ 190°C & 21.6 kg load	46	g/10 min	ISO 1133
<b>Density at 23°C</b>	961	kg/m <sup>3</sup>	ASTM D1505
<b>MECHANICAL PROPERTIES <sup>(2)</sup></b>			
<b>1% Secant Modulus</b>	>1000	MPa	ASTM D638
<b>Tensile Strength at Yield</b>	30	MPa	ASTM D638
<b>Tensile Strength at Break</b>	18	MPa	ASTM D638
<b>Tensile Elongation at Break</b>	500	%	ASTM D638
<b>Flexural Strength</b>	28	MPa	ASTM D790
<b>Flexural Modulus</b>	1100	MPa	ISO 178/1A
<b>Izod Impact Strength</b>	150	J/m	ASTM D256
<b>Hardness (Shore D)</b>	66	-	ASTM D2240
<b>THERMAL PROPERTIES</b>			
<b>Vicat Softening Point</b>	127	°C	ASTM D1525
<b>Brittleness Temperature</b>	<-75	°C	ASTM D746