

SABIC® HDPE CC027C

HIGH DENSITY POLYETHYLENE FOR CAPS & CLOSURES

DESCRIPTION

CC027C is a multimodal, high density polyethylene. It offers very good process ability in combination with stiffness, impact resistance, excellent ESCR and organoleptic properties. This grade is intended for injection and compression molding closures for sparkling water and carbonated soft drinks, particularly for latest designs of lightweight.

CC027C does not contain slip agent.

TYPICAL APPLICATIONS

-Caps & Closures for Carbonated Soft Drinks (CSD), sparkling water and other carbonated beverages.

-Caps & Closures for beverage, food and personal care packaging with high ESCR requirements.

This product is not intended for and must not be used in any pharmaceutical/medical applications.

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR)			
@ 190°C & 2.16 kg load	0.8	g/10 min	ASTM D1238
MECHANICAL PROPERTIES			
Tensile test ^{(1) (2)}			
Tensile modulus	1100	MPa	ISO 527-2
Stress at Yield	26	MPa	ISO 527-2
Strain at Yield	9	%	ISO 527-2
Charpy Impact Strength ⁽³⁾			
23°C, Type 1, Notch A	9	kJ/m ²	ISO 179-1
ESCR ⁽³⁾			
10% Igepal, F50	250	Hrs	ASTM D1693B
FNCT (6.0 MPa, 2% Arkopal N100, 50 °C)	32	Hrs	ISO 16770
Strain Hardening, Gp	19	MPa	ISO 18488
C&C PROPERTIES			
Organoleptic properties	Approved	-	SABIC method

(1) Test specimen according to ISO 527-2 type 1BA, thickness 2 mm

(2) Speed of testing: 50 mm/min

(3) Compression molding of test specimen according to ISO 17855-2

PROCESSING CONDITIONS

Barrel temperature: 180-240°C (356-464°F)

Mold temperature: 10-40°C (50-104°F)