

# SABIC® HDPE F04660

## HIGH DENSITY POLYETHYLENE

### DESCRIPTION

SABIC® HDPE F04660 is a homopolymer film grade with a broad processing window and high stiffness. It has good moisture barrier properties and can be blended with LDPE and LLDPE to improve film strength and rigidity.

This product is not intended for and must not be used in any pharmaceutical/medical applications.

### TYPICAL APPLICATIONS

SABIC® HDPE F04660 is typically used for applications where high stiffness is required. It can be used in the middle layer in a coex structure or blended with LDPE and LLDPE to increase stiffness and mechanical properties. It has good water vapor barrier properties required for certain food packaging.

### TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES</b>			
<b>Melt Flow Rate (MFR)</b>			
at 190 °C and 21.6 kg	46	dg/min	ASTM D1238
at 190 °C and 2.16 kg	0.7	dg/min	ASTM D1238
at 190 °C and 5 kg	3	dg/min	ISO 1133
<b>Density</b>	961	kg/m <sup>3</sup>	ASTM D1505
<b>MECHANICAL PROPERTIES</b>			
<b>Tensile test</b>			
stress at break	18	MPa	ISO 527-2
tensile modulus	1250	MPa	ISO 527-2
stress at yield	29	MPa	ISO 527-2
<b>Tensile test</b> <sup>(1) (2)</sup>			
strain at break	>1000	%	ISO 527-2
<b>Flexural test</b>			
Flexural modulus	1550	MPa	ISO 178
Flexural strength	31	MPa	ISO 178
<b>Izod impact notched</b>			
at -30 °C	6	kJ/m <sup>2</sup>	ISO 180/A
at 23 °C	10	kJ/m <sup>2</sup>	ISO 180/A
<b>Hardness Shore D</b>	63	-	ISO 868
<b>ESCR (10% Igepal CO-630), F50</b>	15	h	ASTM D1693B
<b>FILM PROPERTIES</b> <sup>(3)</sup>			
<b>Dart Impact F50</b>	<20	g	ASTM D1709
<b>Tear strength TD Elmendorf</b>	800	g/μm	ASTM D1922
<b>Tear strength MD Elmendorf</b>	10	g/μm	ASTM D1922
<b>Tensile test film</b> <sup>(4)</sup>			
Strain at break TD	3	%	ASTM D882
Modulus of elasticity TD	1700	MPa	ASTM D882
Stress at break MD	67	MPa	ASTM D882
Stress at break TD	37	MPa	ASTM D882

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Modulus of elasticity MD	1250	MPa	ASTM D882
Strain at break MD	490	%	ASTM D882
<b>THERMAL PROPERTIES</b>			
Heat deflection temperature			
at 0.45 MPa (HDT/B)	88	°C	ISO 75-2
Vicat Softening Temperature <sup>(5) (6)</sup>	129	°C	ASTM D1525
Vicat softening temperature			
at 10 N (VST/A)	129	°C	ISO 306
<b>DSC test</b>			
melting point	134	°C	ISO 11357-3
enthalpy change	223	J/g	ISO 11357-3

(1) Test specimen according to ISO 527-2 type 1BA, thickness 2 mm

(2) Speed of testing: 50 mm/min

(3) Properties are based on 25 µm film produced at 2.5:1 BUR using 100% F04660.

(4) Film properties have been measured on 25 µm blown film with a BUR of 4.

(5) Compression moulding of test specimen according to ISO 1872-2

(6) Conditioning of test specimen: temp. 23 °C, relative humidity 50 %, 24 hours

## PROCESSING CONDITIONS

SABIC® HDPE F04660 can be extruded at melt temperatures between 190 and 220 °C.