

# SABIC® HDPE M40060

## HIGH DENSITY POLYETHYLENE

### DESCRIPTION

M40060 is High Density Polyethylene grade with narrow molecular weight distribution suitable for injection molding applications. It has been designed to give good rigidity, excellent toughness and low warp age.

### TYPICAL APPLICATIONS

M40060 series grades are recommended for industrial pails, shipping containers and other parts requiring balance of toughness and rigidity.

### TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES</b>			
Melt Flow Rate (MFR)			
@ 190°C & 2.16 kg load	4	g/cc	ASTM D1238
<b>MECHANICAL PROPERTIES</b>			
1% Secant Modulus <sup>(2)</sup>	950	MPa	ASTM D638
Tensile Strength at Yield	24	MPa	ASTM D638
Tensile Strength at Break	22	MPa	ASTM D638
Tensile Elongation at Break	>600	%	ASTM D638
Flexural Strength	24	MPa	ASTM D790
Flexural Modulus	900	MPa	ISO 178/1A
Izod Impact Strength	180	J/m	ASTM D256
Hardness (Shore D)	60	-	ASTM D2240
ESCR (100% Igepal), F50 <sup>(3)</sup>	6	Hrs	ASTM D1693B
ESCR (10% Igepal), F50	3	Hrs	ASTM D1693B
<b>THERMAL PROPERTIES</b>			
Vicat Softening Point	125	°C	ASTM D1525
Brittleness Temperature	<-75	°C	ASTM D746

(1) Typical values: not to be construed as specification limits.

(2) Based on Injection molded specimens.

(3) Based on compression molded sheet

### PROCESSING CONDITIONS

Typical processing conditions for M40060 are: Melt temperature: 190-250°C Mold temperature: 15-60°C