



# SABIC® LDPE 2402H0

## LOW DENSITY POLYETHYLENE

### DESCRIPTION

SABIC® LDPE 2402H0 is a blown film grade which has a very broad processing window and an excellent draw down ability. The films are characterized by very good mechanical and optical properties. The grade contains no additives.

#### Application

SABIC® LDPE 2402H0 is typically used for thin film applications where enhanced stiffness is required, such as thin shrink films, food packaging films, bags and pouches.

#### Film properties

Film properties have been measured at film of 25 µm with a BUR of 3.

The film has been produced on Kiefel IBC blown film line with 200 kg/h. Die size 200 mm, die gap 0.8 mm.

This product is not intended for and must not be used in any pharmaceutical/medical applications.

### TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES</b>			
<b>Melt Flow Rate (MFR)</b>			
at 190 °C and 2.16 kg	2	dg/min	ISO 1133
<b>Density</b>	924	kg/m³	ISO 1183
<b>OPTICAL PROPERTIES</b>			
<b>Gloss (45°)</b>	60	%	ASTM D2457
<b>Haze</b>	7	%	ASTM D1003
<b>FILM PROPERTIES</b>			
<b>Impact strength</b>	20	kJ/m	ASTM D4272
<b>Tear strength TD</b>	35	kN/m	ISO 6383-2
<b>Tear strength MD</b>	80	kN/m	ISO 6383-2
<b>Tensile test film</b>			
Stress at break TD	20	MPa	ISO 527-3
Stress at break MD	30	MPa	ISO 527-3
Yield stress TD	12	MPa	ISO 527-3
Modulus of elasticity TD	240	MPa	ISO 527-3
<b>Tensile test film</b>			
Strain at break MD	>200	%	ISO 527-3
Strain at break TD	>500	%	ISO 527-3
<b>Coefficient of friction</b>	1.0	-	ASTM D1894
<b>Blocking</b>	20	g	SABIC method
<b>Re-blocking</b>	<5	g	SABIC method
<b>THERMAL PROPERTIES</b>			
<b>Vicat Softening Temperature</b>			
at 10 N (VST/A)	96	°C	ISO 306