

SABIC® LLDPE 118WJ

LINEAR LOW DENSITY POLYETHYLENE

DESCRIPTION

SABIC® LLDPE 118WJ is a butene linear low density polyethylene resin typically used for general purpose applications. Films produced from this resin are tough with good puncture resistance, high tensile strength and good hottack properties. The resin contains slip and antiblock additive. SABIC® LLDPE 118WJ is TNPP free.

This product is not intended for and must not be used in any pharmaceutical/medical applications.

TYPICAL APPLICATIONS

Shipping sacks, ice bags, frozen food bags, stretch wrap film, produce bags, liners, carrier bags, garbage bags, agricultural films, laminated and coextruded films for meat wrap, frozen food and other food packaging, shrink film (for blending with LDPE), industrial consumer packaging, and high clarity film applications if blended with (10~20%) LDPE.

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR)			
at 190 °C and 2.16 kg	1.0	dg/min	ISO 1133
Density	918	kg/m ³	ASTM D1505
OPTICAL PROPERTIES⁽¹⁾			
Gloss (45°)	42	%	ASTM D2457
Haze ⁽¹⁾	20	%	ASTM D1003
FILM PROPERTIES⁽¹⁾			
Impact strength	22	kJ/m	ASTM D4272
Tear strength TD	120	kN/m	ISO 6383-2
Tear strength MD	40	kN/m	ISO 6383-2
Tensile test film			
Strain at break TD	800	%	ISO 527-3
Strain at break MD	600	%	ISO 527-3
Modulus of elasticity MD	160	MPa	ISO 527-3
Modulus of elasticity TD	180	MPa	ISO 527-3
Stress at break TD	30	MPa	ISO 527-3
Yield stress TD	11	MPa	ISO 527-3
Stress at break MD	37	MPa	ISO 527-3
Coefficient of friction	0.1	-	ASTM D1894
Blocking	15	g	SABIC method
Re-blocking	10	g	SABIC method
THERMAL PROPERTIES			
Vicat Softening Temperature			
at 10 N (VST/A)	101	°C	ISO 306
DSC test			
melting point	121	°C	SABIC method

(1) Properties have been measured by producing 30 µm film with 2.5 BUR using 100% 118WJ.