



SABIC® LLDPE 118WSJ

LINEAR LOW DENSITY POLYETHYLENE

DESCRIPTION

118WSJ is a butene Linear Low Density Polyethylene TNPP free grade suitable for general-purpose packaging with high clarity thin gauge film. Films produced from these resins are tough with excellent puncture resistance, high tensile strength and good hot tack properties.

TYPICAL APPLICATIONS

Shipping sacks, ice bags, frozen food bags, stretch wrap film, produce bags, liners, carrier bags, garbage bags, agricultural films, laminated and coextruded films for meat wrap, frozen food and other food packaging, shrink film (for blending with LDPE), industrial consumer packaging, and high clarity film applications if blended with (10-20%) LDPE.

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR)			
190°C and 2.16 kg	1	g/10 min	ASTM D1238
Density	918	kg/m ³	ASTM D1505
FORMULATION			
Slip agent	☑	-	-
Anti block agent	☑	-	-
MECHANICAL PROPERTIES			
Dart Impact Strength	145	g/μm	ASTM D1709
OPTICAL PROPERTIES			
Haze	10	%	ASTM D1003
Gloss			
at 60°	60	-	ASTM D2457
FILM PROPERTIES			
Tensile Properties ⁽¹⁾			
stress at break, MD	40	MPa	ASTM D882
stress at break, TD	32	MPa	ASTM D882
strain at break, MD	750	%	ASTM D882
strain at break, TD	800	%	ASTM D882
stress at yield, MD	11	MPa	ASTM D882
stress at yield, TD	12	MPa	ASTM D882
1% secant modulus, MD	220	MPa	ASTM D882
1% secant modulus, TD	260	MPa	ASTM D882
Puncture resistance	68	J/mm	SABIC method
Elmendorf Tear Strength			
MD	165	g	ASTM D1922
TD	300	g	ASTM D1922
THERMAL PROPERTIES			
Vicat Softening Temperature	100	°C	ASTM D1525