

# SABIC® LLDPE 218WJ

LINEAR LOW DENSITY POLYETHYLENE

## DESCRIPTION

218WJ is a butene Linear Low Density Polyethylene TNPP free grade suitable for general-purpose packaging. It is easy to process giving good tensile properties, impact strength and optical properties. 218WJ contains slip and antiblock additives.

## TYPICAL APPLICATIONS

Lamination film, thin liners, shopping bags, carrier bags, garbage bags, coextruded films, consumer packaging and other general-purpose applications.

## TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES</b>			
<b>Melt Flow Rate (MFR)</b>			
at 190°C and 2.16 kg	2	g/10 min	ASTM D1238
<b>Density</b>	918	kg/m <sup>3</sup>	ASTM D1505
<b>FORMULATION</b>			
Slip agent	<input checked="" type="checkbox"/>	-	-
Anti block agent	<input checked="" type="checkbox"/>	-	-
<b>MECHANICAL PROPERTIES</b>			
Dart Impact Strength <sup>(1)</sup>	85	g/μm	ASTM D1709
<b>OPTICAL PROPERTIES <sup>(1)</sup></b>			
Haze	13	%	ASTM D1003
Gloss			
at 60°	80	-	ASTM D2457
<b>FILM PROPERTIES <sup>(1)</sup></b>			
<b>Tensile Properties</b>			
stress at break, MD	35	MPa	ASTM D882
stress at break, TD	29	MPa	ASTM D882
strain at break, MD	700	%	ASTM D882
strain at break, TD	750	%	ASTM D882
stress at yield, MD	12	MPa	ASTM D882
stress at yield, TD	10	MPa	ASTM D882
1% secant modulus, MD	220	MPa	ASTM D882
1% secant modulus, TD	260	MPa	ASTM D882
<b>Elmendorf Tear Strength</b>			
MD	130	g	ASTM D1922
TD	320	g	ASTM D1922
<b>THERMAL PROPERTIES</b>			
Vicat Softening Point	98	°C	ASTM D1525

(1) Mechanical properties have been measured by producing 30 μ film with 2.5 BUR using 100% 218N.