

# SABIC® LLDPE 222WT

LINEAR LOW DENSITY POLYETHYLENE  
REGION ASIA

## DESCRIPTION

SABIC® 222WT is an ethylene-butene copolymer designed for blown film application. 222WT has superior film mechanical property like stiffness, puncture resistance and tensile strength, it also has excellent sealing property, 222WT contains high slip and high antiblock.

## TYPICAL APPLICATIONS

Cloth bag, carrier bag, thin layer coating, refuse bag, meat packaging and other food packaging or lamination film ,general purpose consumer packaging etc.

## TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES</b>			
<b>Melt Flow Rate (MFR)</b>			
@ 190°C & 2.16 kg	1.9	g/10 min	ASTM D1238
<b>Density at 23°C</b>	922	kg/m <sup>3</sup>	ASTM D1505
<b>FORMULATION</b>			
Slip agent	<input checked="" type="checkbox"/>	-	-
Anti block agent	<input checked="" type="checkbox"/>	-	-
<b>MECHANICAL PROPERTIES</b>			
<b>Tensile test</b>			
stress at yield, MD	10	MPa	ASTM D882
stress at yield, TD	10	MPa	ASTM D882
stress at break, MD	31	MPa	ASTM D882
stress at break, TD	23	MPa	ASTM D882
elongation at break, MD	450	%	ASTM D882
elongation at break, TD	600	%	ASTM D882
<b>OPTICAL PROPERTIES</b>			
<b>Gloss</b>			
45°	50	-	ASTM D2457
Haze <sup>(1)</sup>	16	%	ASTM D1003
<b>FILM PROPERTIES</b>			
<b>Dart Impact F50</b>	112	g	ASTM D1709

(1) Properties have been measured by producing 30  $\mu$  film with 2 BUR using 100% 222WT.

## PROCESSING CONDITIONS

Typical processing conditions for 222WT are:

Barrel temperature: 190 - 220°C

Blow up ratio: 2.0 - 3.0