

# SABIC® LLDPE 318BJA

LINEAR LOW DENSITY POLYETHYLENE  
REGION AMERICAS

## DESCRIPTION

SABIC® LLDPE 318BJA is a butene linear low density polyethylene resin typically designed for easy processing and specially formulated for optimum thermal stability at high temperatures used in cast film extrusion. Cast film produced from SABIC® LLDPE 318BJA exhibit excellent optical properties, puncture resistance and tear strength. SABIC® LLDPE 318BJA is TNPP free.

This product is not intended for and must not be used in any pharmaceutical/medical applications.

## TYPICAL APPLICATIONS

SABIC® LLDPE 318BJA resin is typically used for hand and pallet stretch wrap, cling film, melt embossed film and other genera-purpose application.

## TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES</b>			
Melt Flow Rate (MFR)			
at 190 °C and 2.16 kg	2.8	g/10 min	ASTM D1238
Density	918	kg/m <sup>3</sup>	ASTM D1505
<b>OPTICAL PROPERTIES<sup>(1) (2)</sup></b>			
Haze	2.0	%	ASTM D1003
Gloss (45°)	96	%	ASTM D2457
<b>FILM PROPERTIES</b>			
Tensile test film <sup>(1) (2)</sup>			
Stress at break MD	40	MPa	ASTM D882
Stress at break TD	20	MPa	ASTM D882
Strain at break MD	500	%	ASTM D882
Strain at break TD	800	%	ASTM D882
Dart Impact Strength	60	g	ASTM D1709
Stress at yield MD	13	MPa	ASTM D853
Stress at yield TD	10	MPa	ASTM D882
Secant modulus 1% MD	135	MPa	ASTM D882
Secant modulus 1% TD	140	MPa	ASTM D882
Puncture Force	40	N	SABIC method
Puncture Energy	1.9	J	SABIC method
Elmendorf Tear Strength MD	65	g	ASTM D1922
Elmendorf Tear Strength TD	300	g	ASTM D1922
<b>THERMAL PROPERTIES</b>			
DSC test			
Melting point	121	°C	SABIC method

(1) Typical values: not to be construed as specification limits.

(2) Cast film processing conditions: Film thickness 35 lm, Die Gap 31.5mil (0.8 mm), Melt Temperature 235C, Chill Roll Temperature: 180C, and Haul Off Speed 15m/min