



LNP™ STAT-KON™ Compound PFD06

Americas: COMMERCIAL

Also known as: LNP™ STAT-KON™ Compound PF-30

Product reorder name: PFD06

LNP STAT-KON PFD06 is a compound based on Nylon 6 resin containing 30% Glass Fiber. Added features of this material include: Electrically Conductive.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, break	1620	kgf/cm ²	ASTM D 638
Tensile Strain, break	2.3	%	ASTM D 638
Tensile Modulus, 50 mm/min	119500	kgf/cm ²	ASTM D 638
Flexural Stress	2460	kgf/cm ²	ASTM D 790
Flexural Modulus	112400	kgf/cm ²	ASTM D 790
IMPACT			
Izod Impact, unnotched, 23°C	92	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	10	cm-kgf/cm	ASTM D 256
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	206	°C	ASTM D 648
PHYSICAL			
Density	1.43	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.5	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.4	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	1.2	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs (5)	0.38	%	ISO 294
Mold Shrinkage, xflow, 24 hrs (5)	1.15	%	ISO 294
Moisture Absorption (23°C / 50% RH)	0.91	%	ISO 62
ELECTRICAL			
Volume Resistivity	1.E+03	Ohm-cm	ASTM D 257
Surface Resistivity	1.E+00 - 6.E+00	Ohm	ASTM D 257



LNP™ STAT-KON™ Compound PFD06

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.15 - 0.25	%
Melt Temperature	265 - 275	°C
Front - Zone 3 Temperature	275 - 290	°C
Middle - Zone 2 Temperature	265 - 275	°C
Rear - Zone 1 Temperature	250 - 260	°C
Mold Temperature	80 - 95	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	30 - 60	rpm