



LNP™ THERMOCOMP™ Compound PF00C

Americas: COMMERCIAL

Also known as: LNP™ THERMOCOMP™ Compound PF-100-12

Product reorder name: PF00C

LNP THERMOCOMP PF00C is a compound based on Nylon 6 resin containing 60% Glass Fiber.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, break	2150	kgf/cm ²	ASTM D 638
Tensile Strain, break	2.4	%	ASTM D 638
Tensile Modulus, 50 mm/min	228200	kgf/cm ²	ASTM D 638
Flexural Stress	3720	kgf/cm ²	ASTM D 790
Flexural Modulus	197600	kgf/cm ²	ASTM D 790
IMPACT			
Izod Impact, unnotched, 23°C	125	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	17	cm-kgf/cm	ASTM D 256
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	210	°C	ASTM D 648
PHYSICAL			
Density	1.71	g/cm ³	ASTM D 792



LNP™ THERMOCOMP™ Compound PF00C

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.15 - 0.25	%
Melt Temperature	265 - 275	°C
Front - Zone 3 Temperature	275 - 290	°C
Middle - Zone 2 Temperature	265 - 275	°C
Rear - Zone 1 Temperature	250 - 260	°C
Mold Temperature	80 - 95	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	30 - 60	rpm