

# LNPT<sup>TM</sup> LUBRICOMP<sup>TM</sup> COMPOUND RAL22

RAL-4022  
REGION ASIA

## DESCRIPTION

LNP LUBRICOMP RAL22 compound is based on Nylon 6/6 resin containing 10% PTFE, 10% aramid fiber. Added features of this grade include: Wear Resistant.

GENERAL INFORMATION	
Features	Wear resistant
Fillers	Aramid Fiber, PTFE
Polymer Types	Polyamide 66 (Nylon 66)
Processing Techniques	Injection Molding

  

INDUSTRY	SUB INDUSTRY
Building and Construction	Building Component
Consumer	Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical

## TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL <sup>(1)</sup></b>			
Tensile Stress, break	81	MPa	ASTM D638
Tensile Strain, break	8.1	%	ASTM D638
Tensile Modulus, 5 mm/min	3440	MPa	ASTM D638
Flexural Stress	113	MPa	ASTM D790
Flexural Modulus	2960	MPa	ASTM D790
Tensile Stress, break	79	MPa	ISO 527
Tensile Strain, break	9.5	%	ISO 527
Tensile Modulus, 1 mm/min	3550	MPa	ISO 527
Flexural Stress	117	MPa	ISO 178
Flexural Modulus	3500	MPa	ISO 178
<b>IMPACT <sup>(1)</sup></b>			
Izod Impact, unnotched, 23°C	742	J/m	ASTM D4812
Izod Impact, notched, 23°C	133	J/m	ASTM D256
Instrumented Dart Impact Energy @ peak, 23°C	6	J	ASTM D3763
Multiaxial Impact	1	J	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	48	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	5	kJ/m <sup>2</sup>	ISO 180/1A
<b>THERMAL <sup>(1)</sup></b>			
HDT, 0.45 MPa, 3.2 mm, unannealed	248	°C	ASTM D648

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
HDT, 1.82 MPa, 3.2mm, unannealed	198	°C	ASTM D648
CTE, -40°C to 40°C, flow	7.2E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	8.1E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, flow	7.36E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	8.26E-05	1/°C	ISO 11359-2
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	193	°C	ISO 75/Af
<b>PHYSICAL <sup>(1)</sup></b>			
Density	1.22	g/cm <sup>3</sup>	ASTM D792
Moisture Absorption, (23°C/50% RH/24 hrs)	0.72	%	ASTM D570
Mold Shrinkage, flow, 24 hrs <sup>(2)</sup>	1.9	%	ASTM D955
Mold Shrinkage, xflow, 24 hrs <sup>(2)</sup>	2	%	ASTM D955
Mold Shrinkage, flow, 24 hrs <sup>(2)</sup>	1.92	%	ISO 294
Mold Shrinkage, xflow, 24 hrs <sup>(2)</sup>	1.95	%	ISO 294
Wear Factor Washer	13	10 <sup>-4</sup> -10 in <sup>4</sup> -min/ft-lb-hr	ASTM D3702 Modified: Manual
Dynamic COF	0.54	-	ASTM D3702 Modified: Manual
Static COF	0.45	-	ASTM D3702 Modified: Manual
Density	1.22	g/cm <sup>3</sup>	ISO 1183
Moisture Absorption (23°C / 50% RH)	1.17	%	ISO 62
<b>INJECTION MOLDING <sup>(3)</sup></b>			
Drying Temperature	80	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.15 – 0.25	%	
Melt Temperature	275 – 290	°C	
Front - Zone 3 Temperature	295 – 305	°C	
Middle - Zone 2 Temperature	280 – 295	°C	
Rear - Zone 1 Temperature	265 – 275	°C	
Mold Temperature	80 – 95	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	