

LNPTM LUBRICOMPTM COMPOUND RAL229

RAL-4022 FR

DESCRIPTION

LNP LUBRICOMP RAL229 compound is based on Nylon 6/6 resin containing 10% aramid fiber, 10% PTFE. Added features of this grade include: Flame Retardant, Wear Resistant.

GENERAL INFORMATION

Features	Flame Retardant, Wear resistant
Fillers	Aramid Fiber, PTFE
Polymer Types	Polyamide 66 (Nylon 66)
Processing Techniques	Injection Molding

INDUSTRY

SUB INDUSTRY

Building and Construction	Building Component
Consumer	Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL⁽¹⁾			
Tensile Stress, brk, Type I, 5 mm/min	81	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	4	%	ASTM D638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	114	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	3720	MPa	ASTM D790
IMPACT⁽¹⁾			
Izod Impact, notched, 23°C	37	J/m	ASTM D256
THERMAL⁽¹⁾			
HDT, 1.82 MPa, 3.2mm, unannealed	162	°C	ASTM D648
Relative Temp Index, Elec ⁽²⁾	65	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽²⁾	65	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽²⁾	65	°C	UL 746B
PHYSICAL⁽¹⁾			
Specific Gravity	1.42	-	ASTM D792
FLAME CHARACTERISTICS⁽²⁾			
UL Yellow Card Link	E121562-101282579	-	-
UL Recognized, 94V-0 Flame Class Rating	≥3	mm	UL 94
INJECTION MOLDING⁽³⁾			
Drying Temperature	80	°C	
Drying Time	4	Hrs	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Maximum Moisture Content	0.15 – 0.25	%	
Melt Temperature	275 – 290	°C	
Front - Zone 3 Temperature	295 – 305	°C	
Middle - Zone 2 Temperature	280 – 295	°C	
Rear - Zone 1 Temperature	265 – 275	°C	
Mold Temperature	80 – 95	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	