

LNPTM LUBRICOMPTM COMPOUND RAL32

RAL-4032

DESCRIPTION

LNP LUBRICOMP RAL32 compound is based on Nylon 6/6 resin containing 10% aramid fiber, 15% PTFE. Added features of this grade include: Wear Resistant.

GENERAL INFORMATION	
Features	Wear resistant
Fillers	Aramid Fiber, PTFE
Polymer Types	Polyamide 66 (Nylon 66)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Building and Construction	Building Component
Consumer	Sport / Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, brk, Type I, 5 mm/min	83	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	5.9	%	ASTM D638
Tensile Modulus, 5 mm/min	3840	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	124	MPa	ASTM D790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	123	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	3480	MPa	ASTM D790
Tensile Stress, break, 5 mm/min	78	MPa	ISO 527
Tensile Strain, break, 5 mm/min	6.2	%	ISO 527
Tensile Modulus, 1 mm/min	3860	MPa	ISO 527
Flexural Stress	113	MPa	ISO 178
Flexural Modulus, 2 mm/min	3470	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, unnotched, 23°C	472	J/m	ASTM D4812
Izod Impact, notched, 23°C	46	J/m	ASTM D256
Multiaxial Impact	1	J	ISO 6603
Instrumented Dart Impact Total Energy, 23°C	3	J	ASTM D3763
Izod Impact, unnotched 80°10°4 +23°C	28	kJ/m²	ISO 180/1U
Izod Impact, notched 80°10°4 +23°C	3	kJ/m²	ISO 180/1A
THERMAL ⁽¹⁾			
HDT, 0.45 MPa, 3.2 mm, unannealed	254	°C	ASTM D648

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
HDT, 1.82 MPa, 3.2mm, unannealed	208	°C	ASTM D648
CTE, -30°C to 30°C, flow	6.3E-05	1/°C	ASTM D696
CTE, -30°C to 30°C, xflow	8.2E-05	1/°C	ASTM D696
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	242	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	115	°C	ISO 75/Af
PHYSICAL ⁽¹⁾			
Specific Gravity	1.25	-	ASTM D792
Density	1.25	g/cm ³	ASTM D792
Moisture Absorption, (23°C/50% RH/24 hrs)	0.74	%	ASTM D570
Mold Shrinkage, flow, 24 hrs ⁽²⁾	0.9 – 2	%	ASTM D955
Mold Shrinkage, xflow, 24 hrs ⁽²⁾	1 – 3	%	ASTM D955
Wear Factor Washer	12	10 ⁻¹⁰ in ⁴ -min/ft-lb-hr	ASTM D3702 Modified: Manual
Wear Factor Ring	0	10 ⁻¹⁰ in ⁴ -min/ft-lb-hr	ASTM D3702 Modified: Manual
Dynamic COF	0.34	-	ASTM D3702 Modified: Manual
Static COF	0.3	-	ASTM D3702 Modified: Manual
Moisture Absorption (23°C / 50% RH)	1.1	%	ISO 62
INJECTION MOLDING ⁽³⁾			
Drying Temperature	80	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.15 – 0.25	%	
Melt Temperature	275 – 290	°C	
Front - Zone 3 Temperature	295 – 305	°C	
Middle - Zone 2 Temperature	280 – 295	°C	
Rear - Zone 1 Temperature	265 – 275	°C	
Mold Temperature	80 – 95	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	