

# LNPTM LUBRICOMPTM COMPOUND RFL36SXC

RFL-4036

## DESCRIPTION

LNP LUBRICOMP RFL36SXC compound is based on Nylon 6/6 resin containing 30% glass fiber, 15% PTFE. Added features of this grade include: Heat Stabilized, Wear Resistant.

GENERAL INFORMATION				
<b>Features</b>				Heat Stabilized, Wear resistant
<b>Fillers</b>				Glass Fiber, PTFE
<b>Polymer Types</b>				Polyamide 66 (Nylon 66)
<b>Processing Techniques</b>				Injection Molding
INDUSTRY		SUB INDUSTRY		
Building and Construction		Building Component		
Consumer		Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance		
Electrical and Electronics		Mobile Phone - Computer - Tablets		
Industrial		Electrical		
TYPICAL PROPERTY VALUES				
PROPERTIES		TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL<sup>(1)</sup></b>				
Tensile Stress, break, 5 mm/min		173	MPa	ISO 527
Tensile Strain, break, 5 mm/min		3	%	ISO 527
Tensile Modulus, 1 mm/min		9700	MPa	ISO 527
Flexural Stress, break, 2 mm/min		238	MPa	ISO 178
Flexural Modulus, 2 mm/min		7900	MPa	ISO 178
<b>IMPACT<sup>(1)</sup></b>				
Izod Impact, unnotched 80*10*4 +23°C		70	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C		13	kJ/m <sup>2</sup>	ISO 180/1A
<b>THERMAL<sup>(1)</sup></b>				
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm		261	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm		249	°C	ISO 75/Af
<b>PHYSICAL<sup>(1)</sup></b>				
Mold Shrinkage on Tensile Bar, flow <sup>(2)</sup>		0.2 – 0.4	%	SABIC method
Density		1.49	g/cm <sup>3</sup>	ISO 1183
<b>INJECTION MOLDING<sup>(3)</sup></b>				
Drying Time		4	Hrs	
Drying Temperature		80	°C	
Melt Temperature		280 – 305	°C	
Rear - Zone 1 Temperature		265 – 275	°C	
Middle - Zone 2 Temperature		280 – 295	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Front - Zone 3 Temperature	295 – 305	°C	
Maximum Moisture Content	0.15 – 0.25	%	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	
Mold Temperature	95 – 110	°C	