

LNPTTM LUBRICOMPTTM COMPOUND RFL36SXD

DESCRIPTION

LNP LUBRICOMP RFL36SXD compound is based on Nylon 6/6 resin containing 30% glass fiber, 15% PTFE. Added features of this grade include: Internally Lubricated, Wear Resistant, Heat Stabilized

GENERAL INFORMATION	
Features	Heat Stabilized, Wear resistant, High stiffness/Strength
Fillers	Glass Fiber, PTFE
Polymer Types	Polyamide 66 (Nylon 66)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Automotive	Automotive Under the Hood
Consumer	Commercial Appliance
Electrical and Electronics	Electronic Components, Mobile Phone - Computer - Tablets
Industrial	Electrical

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, break, 5 mm/min	173	MPa	ISO 527
Tensile Strain, break, 5 mm/min	3	%	ISO 527
Tensile Modulus, 1 mm/min	9700	MPa	ISO 527
Flexural Stress, break, 2 mm/min	238	MPa	ISO 178
Flexural Modulus, 2 mm/min	7900	MPa	ISO 178
IMPACT			
Izod Impact, unnotched 80*10*4 +23°C	70	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	13	kJ/m ²	ISO 180/1A
THERMAL			
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	261	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	249	°C	ISO 75/Af
PHYSICAL			
Mold Shrinkage on Tensile Bar, flow	0.2 – 0.4	%	SABIC method
Density	1.49	g/cm ³	ISO 1183
INJECTION MOLDING			
Drying Temperature	80	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.15 – 0.25	%	
Melt Temperature	280 – 305	°C	
Rear - Zone 1 Temperature	265 – 275	°C	
Middle - Zone 2 Temperature	280 – 295	°C	



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Front - Zone 3 Temperature	295 – 305	°C	
Mold Temperature	95 – 110	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	