

# LNPTM LUBRICOMPTM COMPOUND RFN16SXZ

RFL-4216 HS

## DESCRIPTION

LNP LUBRICOMP RFN16SXZ compound is based on Nylon 6/6 resin containing 30% glass fiber, Molybdenum diSulfide (MoS<sub>2</sub>). Added features of this grade include: Heat Stabilized, Wear Resistant.

### GENERAL INFORMATION

Features	Heat Stabilized, Wear resistant, High stiffness/Strength, No PFAS intentionally added
Fillers	Glass Fiber, Molybdenum
Polymer Types	Polyamide 66 (Nylon 66)
Processing Techniques	Injection Molding

### INDUSTRY

### SUB INDUSTRY

Building and Construction	Building Component
Consumer	Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical

## TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL<sup>(1)</sup></b>			
Tensile Stress, break	160	MPa	ASTM D638
Tensile Strain, break	2.8	%	ASTM D638
Tensile Modulus, 50 mm/min	10680	MPa	ASTM D638
Flexural Stress	246	MPa	ASTM D790
Flexural Modulus	8410	MPa	ASTM D790
Tensile Stress, break	162	MPa	ISO 527
Tensile Strain, break	3	%	ISO 527
Tensile Modulus, 1 mm/min	9900	MPa	ISO 527
Flexural Stress	255	MPa	ISO 178
Flexural Modulus	9800	MPa	ISO 178
<b>IMPACT<sup>(1)</sup></b>			
Izod Impact, unnotched, 23°C	865	J/m	ASTM D4812
Izod Impact, notched, 23°C	80	J/m	ASTM D256
Instrumented Dart Impact Energy @ peak, 23°C	9	J	ASTM D3763
Multiaxial Impact	2	J	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	57	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	8	kJ/m <sup>2</sup>	ISO 180/1A
<b>THERMAL<sup>(1)</sup></b>			
HDT, 0.45 MPa, 3.2 mm, unannealed	261	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	249	°C	ASTM D648

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
CTE, -40°C to 40°C, flow	3.06E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	6.3E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, flow	3.16E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	6.31E-05	1/°C	ISO 11359-2
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	220	°C	ISO 75/Af
<b>PHYSICAL<sup>(1)</sup></b>			
Density	1.41	g/cm <sup>3</sup>	ASTM D792
Moisture Absorption, (23°C/50% RH/24 hrs)	0.65	%	ASTM D570
Mold Shrinkage, flow, 24 hrs <sup>(2)</sup>	0.3	%	ASTM D955
Mold Shrinkage, xflow, 24 hrs <sup>(2)</sup>	1.3	%	ASTM D955
Mold Shrinkage, flow, 24 hrs <sup>(2)</sup>	0.28	%	ISO 294
Mold Shrinkage, xflow, 24 hrs <sup>(2)</sup>	1.34	%	ISO 294
Wear Factor Washer	159	10 <sup>8</sup> -10 in <sup>5</sup> -min/ft-lb-hr	ASTM D3702 Modified: Manual
Dynamic COF	0.43	-	ASTM D3702 Modified: Manual
Static COF	0.48	-	ASTM D3702 Modified: Manual
Density	1.41	g/cm <sup>3</sup>	ISO 1183
Moisture Absorption (23°C / 50% RH)	1.14	%	ISO 62
<b>INJECTION MOLDING<sup>(3)</sup></b>			
Drying Temperature	80	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.15 – 0.25	%	
Melt Temperature	280 – 305	°C	
Front - Zone 3 Temperature	295 – 305	°C	
Middle - Zone 2 Temperature	280 – 295	°C	
Rear - Zone 1 Temperature	265 – 275	°C	
Mold Temperature	95 – 110	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	