

LNPTTM LUBRICOMPTTM COMPOUND RFN17SXS

RFL-4217 HS

DESCRIPTION

LNP LUBRICOMP RFN17SXS compound is based on Nylon 6/6 resin containing 35% glass fiber, Molybdenum diSulfide (MoS₂). Added features of this grade include: Heat Stabilized, Wear Resistant.

GENERAL INFORMATION	
Features	Heat Stabilized, Wear resistant, High stiffness/Strength
Fillers	Glass Fiber, Molybdenum
Polymer Types	Polyamide 66 (Nylon 66)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Building and Construction	Building Component
Consumer	Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yield, 5 mm/min	214	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.7	%	ISO 527
Tensile Modulus, 1 mm/min	12300	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	286	MPa	ISO 178
Flexural Modulus, 2 mm/min	9750	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, unnotched 80*10*4 +23°C	70	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	11	kJ/m ²	ISO 180/1A
THERMAL ⁽¹⁾			
CTE, 23°C to 60°C, flow	2.50E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	8.70E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	262	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	253	°C	ISO 75/Af
PHYSICAL ⁽¹⁾			
Mold Shrinkage, flow ⁽²⁾	0.1 – 0.3	%	SABIC method
Density	1.45	g/cm ³	ISO 1183
Water Absorption, (23°C/24hrs)	0.84	%	ISO 62-1
INJECTION MOLDING ⁽³⁾			
Drying Temperature	80	°C	
Drying Time	4	Hrs	



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Maximum Moisture Content	0.15 – 0.25	%	
Melt Temperature	280 – 305	°C	
Front - Zone 3 Temperature	295 – 305	°C	
Middle - Zone 2 Temperature	280 – 295	°C	
Rear - Zone 1 Temperature	265 – 275	°C	
Mold Temperature	95 – 110	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	